


OIL ANALYSIS REPORT

Sample Rating Trend









Machine Id **620M** Component **Diesel Engine**

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFOR	MAT <u>ION</u>	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0106652	GFL0087287	GFL0072942
Sample Date		Client Info		02 Jan 2024	19 Jul 2023	11 May 2023
Machine Age	hrs	Client Info		14591	13433	13126
Oil Age	hrs	Client Info		598	351	663
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel	ION	WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method		<1.0 NEG	NEG	NEG
			>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	<1	34	4
Chromium	ppm	ASTM D5185m	>20	0	1	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	<1
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	2	2
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>330	0	<1	1
Tin	ppm	ASTM D5185m	>15	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<1	6	6
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	50	60	60
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	853	969	948
Calcium	ppm	ASTM D5185m	1070	960	1198	1051
Phosphorus	ppm	ASTM D5185m	1150	920	1088	1043
Zinc	ppm	ASTM D5185m	1270	1206	1301	1278
Sulfur	ppm	ASTM D5185m	2060	2826	3710	3892
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	2	10	4
Sodium	ppm	ASTM D5185m		2	5	2
Potassium	ppm	ASTM D5185m	>20	3	0	2
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.4	0.6	0.4
Nitration	Abs/cm	*ASTM D7624	>20	6.6	7.9	7.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.6	19.4	18.4
FLUID DEGRAI	O <u>I</u> TAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.7	15.3	14.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.3	9.2	8.6
Dasc Number (DIV)	my Normy	VOLIMI DE090	0.0	0.5	0.2	0.0



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.2	14.2	13.6

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : FLEET

: GFL0106652 : 06057707

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: 10823656

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 11 Jan 2024

: 11 Jan 2024 Diagnosed Diagnostician : Wes Davis

GFL Environmental - 405 - Arbor Hills

7400 Napier Rd NORTHVILLE, MI US 48168

Contact: Anthony Hopkins

ahopkins@gflenv.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: