

OIL ANALYSIS REPORT

Sample Rating Trend







2126932 Component 2 Differential Fluid GEAR OIL SAE 75W90 (--- GAL)

DIAGNOSIS

FLEET

Recommendation

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 75W90. Please confirm. Please specify the component make and model

with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM		method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0112288		
Sample Date		Client Info		22 Dec 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
		ام م مالح میں			lata a sta	histow 0
CONTAMINATIO	JIN	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG		
WEAR METALS	;	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	257		
Chromium	ppm	ASTM D5185m	>10	4		
Nickel	ppm	ASTM D5185m	>10	10		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	4		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>100	1		
Tin	ppm	ASTM D5185m	>10	2		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	129		
Barium	ppm	ASTM D5185m	200	0		
Molybdenum	ppm	ASTM D5185m	12	0		
Manganese	ppm	ASTM D5185m		16		
Magnesium	ppm	ASTM D5185m	12	2		
Calcium	ppm	ASTM D5185m	150	63		
Phosphorus	ppm	ASTM D5185m	1650	1121		
Zinc	ppm	ASTM D5185m	125	27		
Sulfur	ppm	ASTM D5185m	22500	24171		
CONTAMINANT	ſS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	73		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	4		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	LIGHT		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Free Water	scalar	*Visual		NEG		
·29·16) Rev: 1					Submitted By:	


Report Id: PERDILSC [WUSCAR] 06058418 (Generated: 01/15/2024 15:29:16) Rev: 1

Submitted By: KEVIN HOOKS



OIL ANALYSIS REPORT

FLUID PROPERTIES method limit/base



	Visc @ 40°C	cSt	ASTM D445	109	92.0		nistory2
	SAMPLE IMA	AGES	method	limit/base	current	history1	history2
	Color				no image	no image	no image
Dec22/23	Bottom			L	no image	no image	no image
	GRAPHS			L			
	Ferrous Alloys						
	250 - iron chromium nickel						
	200						
	150-						
	100-						
	50-						
	0						
	Dec22/23			Dec22/23			
	Non-ferrous Me	tais					
	9 - copper lead						
	7-						
	팁 5						
	3						
	Dec22/23			Dec22/23			
	Viscosity @ 40°	С					
	135 130 Abnormal						
	125						
40°C)	115 - Base 5 110 - Base						
- *3	3 100						
	95						
	85 - Abnormal 80 -						
	Dec22/23			Dec22/23			
	: WearCheck USA : PCA0112288 : 06058418 : 10829800 : FLEET	Recieve Diagnos Diagnos	d : 11 J sed : 12 J tician : Wes	an 2024 an 2024 Davis	3	Contact: ł	HWY 9 WE DILLON, 9 US 295 EVIN HOOI
Test Package this sample report, of test methods that a		ervice at 1-8 0 17025 sco	800-237-1369 ope of accredi	tation.	(JCGM 106:2012)	kevin.hooks T:	EVIN HO