

# **OIL ANALYSIS REPORT**

Sample Rating Trend



VISCOSITY



Machine Id **414119** 

Component **Diesel Engine** 

PETRO CANADA DURON SHP 15W40 (--- QTS)

# DIAGNOSIS

### Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

#### Wear

Metal levels are typical for a new component breaking in.

### Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. No other contaminants were detected in the oil.

### ▲ Fluid Condition


The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

| QTS)             |          |             |            |             |             |             |
|------------------|----------|-------------|------------|-------------|-------------|-------------|
| SAMPLE INFORM    | MATION   | method      | limit/base | current     | history1    | history2    |
| Sample Number    |          | Client Info |            | GFL0102586  | GFL0107949  | GFL0102565  |
| Sample Date      |          | Client Info |            | 11 Jan 2024 | 05 Jan 2024 | 13 Dec 2023 |
| Machine Age      | hrs      | Client Info |            | 596         | 562         | 439         |
| Oil Age          | hrs      | Client Info |            | 600         | 0           | 0           |
| Oil Changed      |          | Client Info |            | Changed     | Not Changd  | Not Changd  |
| Sample Status    |          |             |            | ATTENTION   | ATTENTION   | ATTENTION   |
| CONTAMINAT       | ION      | method      | limit/base | current     | history1    | history2    |
| Fuel             |          | WC Method   | >5         | <1.0        | <1.0        | <1.0        |
| Water            |          | WC Method   | >0.2       | NEG         | NEG         | NEG         |
| Glycol           |          | WC Method   |            | NEG         | NEG         | NEG         |
| WEAR METAL       | S        | method      | limit/base | current     | history1    | history2    |
| Iron             | ppm      | ASTM D5185m | >110       | 44          | 43          | 29          |
| Chromium         | ppm      | ASTM D5185m | >4         | <1          | <1          | <1          |
| Nickel           | ppm      | ASTM D5185m | >2         | <1          | 0           | 0           |
| Titanium         | ppm      | ASTM D5185m |            | 0           | 0           | 0           |
| Silver           | ppm      | ASTM D5185m | >2         | 0           | 0           | 0           |
| Aluminum         | ppm      | ASTM D5185m | >25        | 55          | 56          | 47          |
| Lead             | ppm      | ASTM D5185m | >45        | 0           | 0           | <1          |
| Copper           | ppm      | ASTM D5185m |            | 16          | 18          | 15          |
| Tin              | ppm      | ASTM D5185m | >4         | <1          | 0           | 0           |
| Vanadium         | ppm      | ASTM D5185m |            | <1          | 0           | 0           |
| Cadmium          | ppm      | ASTM D5185m |            | 0           | 0           | 0           |
| ADDITIVES        |          | method      | limit/base | current     | history1    | history2    |
| Boron            | ppm      | ASTM D5185m | 0          | 37          | 46          | 45          |
| Barium           | ppm      | ASTM D5185m | 0          | 0           | 0           | 0           |
| Molybdenum       | ppm      | ASTM D5185m | 60         | 14          | 13          | 14          |
| Manganese        | ppm      | ASTM D5185m |            | 4           | 4           | 4           |
| Magnesium        | ppm      | ASTM D5185m | 1010       | 764         | 793         | 826         |
| Calcium          | ppm      | ASTM D5185m | 1070       | 1280        | 1334        | 1421        |
| Phosphorus       | ppm      | ASTM D5185m | 1150       | 740         | 757         | 800         |
| Zinc             | ppm      | ASTM D5185m | 1270       | 867         | 892         | 867         |
| Sulfur           | ppm      | ASTM D5185m | 2060       | 2692        | 3034        | 2868        |
| CONTAMINAN       | IS       | method      | limit/base |             | history1    | history2    |
| Silicon          | ppm      |             | >30        | 24          | 25          | 22          |
| Sodium           | ppm      | ASTM D5185m |            | 6           | 5           | 4           |
| Potassium        | ppm      | ASTM D5185m | >20        | 141         | 144         | 118         |
| INFRA-RED        |          | method      | limit/base | current     | history1    | history2    |
| Soot %           | %        | *ASTM D7844 | >3         | 0.5         | 0.4         | 0.4         |
| Nitration        | Abs/cm   | *ASTM D7624 |            | 10.0        | 9.9         | 9.5         |
| Sulfation        | Abs/.1mm | *ASTM D7415 | >30        | 21.9        | 21.5        | 20.6        |
| FLUID DEGRAE     | OATION   | method      | limit/base | current     | history1    | history2    |
| Oxidation        | Abs/.1mm | *ASTM D7414 | >25        | 19.1        | 18.7        | 17.2        |
| Base Number (BN) | mg KOH/g | ASTM D2896  | 9.8        | 6.0         | 6.2         | 6.4         |



0.0


# **OIL ANALYSIS REPORT**





| VISUAL                  |        | method  | limit/base | current | history1 | history2 |
|-------------------------|--------|---------|------------|---------|----------|----------|
| White Metal             | scalar | *Visual | NONE       | NONE    | NONE     | NONE     |
| Yellow Metal            | scalar | *Visual | NONE       | NONE    | NONE     | NONE     |
| Precipitate             | scalar | *Visual | NONE       | NONE    | NONE     | NONE     |
| Silt                    | scalar | *Visual | NONE       | NONE    | NONE     | NONE     |
| Debris                  | scalar | *Visual | NONE       | NONE    | NONE     | NONE     |
| Sand/Dirt               | scalar | *Visual | NONE       | NONE    | NONE     | NONE     |
| Appearance              | scalar | *Visual | NORML      | NORML   | NORML    | NORML    |
| Odor                    | scalar | *Visual | NORML      | NORML   | NORML    | NORML    |
| <b>Emulsified Water</b> | scalar | *Visual | >0.2       | NEG     | NEG      | NEG      |
| Free Water              | scalar | *Visual |            | NEG     | NEG      | NEG      |


| FLUID PROP   | ERTIES | method    |      |             |             | history       |
|--------------|--------|-----------|------|-------------|-------------|---------------|
| Visc @ 100°C | cSt    | ASTM D445 | 15.4 | <b>11.4</b> | <b>11.4</b> | <b>▲</b> 11.4 |

## **GRAPHS**













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10832000 Test Package : FLEET

: GFL0102586 : 06060618

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved

: 16 Jan 2024 Diagnosed : 17 Jan 2024 Diagnostician : Angela Borella GFL Environmental - 892 - Pauls Valley Hauling 405 East Airport Industrial Road

Pauls Valley, OK US 73075

Contact: Tony Graham tgraham2@wcamerica.com T:

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: