




Machine Id
BLENDER 9
 Component
Gearbox
 Fluid
MOBIL SHC 630 (15 GAL)



DIAGNOSIS

Recommendation
 We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.

Wear
 All component wear rates are normal.

Contamination
 There is a high amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition
 The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PCA0113560	PCA0103591	PCA0094151
Sample Date	Client Info	15 Jan 2024	29 Sep 2023	02 Aug 2023
Machine Age	hrs	0	0	0
Oil Age	hrs	0	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		ABNORMAL	ABNORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.2	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >200	20	3	20
Chromium	ppm ASTM D5185m >15	<1	<1	0
Nickel	ppm ASTM D5185m >15	0	0	0
Titanium	ppm ASTM D5185m	0	0	0
Silver	ppm ASTM D5185m	0	0	0
Aluminum	ppm ASTM D5185m >25	<1	2	<1
Lead	ppm ASTM D5185m >100	0	0	0
Copper	ppm ASTM D5185m >200	0	<1	<1
Tin	ppm ASTM D5185m >25	0	0	0
Vanadium	ppm ASTM D5185m	0	0	<1
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m	7	0	0
Barium	ppm ASTM D5185m	0	0	0
Molybdenum	ppm ASTM D5185m	0	<1	<1
Manganese	ppm ASTM D5185m	1	0	1
Magnesium	ppm ASTM D5185m	2	<1	<1
Calcium	ppm ASTM D5185m	4	<1	<1
Phosphorus	ppm ASTM D5185m	451	465	494
Zinc	ppm ASTM D5185m	<1	<1	5
Sulfur	ppm ASTM D5185m	4306	476	5397

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >50	20	28	22
Sodium	ppm ASTM D5185m	<1	1	1
Potassium	ppm ASTM D5185m >20	1	<1	<1

FLUID CLEANLINESS


method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >10000	▲ 45169	▲ 47967	576
Particles >6µm	ASTM D7647 >2500	▲ 7397	▲ 14083	89
Particles >14µm	ASTM D7647 >640	505	▲ 1739	9
Particles >21µm	ASTM D7647 >160	115	▲ 552	2
Particles >38µm	ASTM D7647 >40	4	28	0
Particles >71µm	ASTM D7647 >10	1	1	0
Oil Cleanliness	ISO 4406 (c) >20/18/16	▲ 23/20/16	▲ 23/21/18	16/14/10

FLUID DEGRADATION


method	limit/base	current	history1	history2
Acid Number (AN) mg KOH/g	ASTM D8045	0.69	0.68	0.67

OIL ANALYSIS REPORT


▲ Particle Trend




▲ Particle Trend



Acid Number




Viscosity @ 40°C



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	217.7	209	221

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------




GRAPHS


Ferrous Alloys




Non-ferrous Metals




Viscosity @ 40°C



▲ Particle Count



Acid Number



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0113560 **Received** : 18 Jan 2024
Lab Number : 06064331 **Diagnosed** : 21 Jan 2024
Unique Number : 10835713 **Diagnostician** : Don Baldrige
Test Package : IND 2 (Additional Tests: PrtCount)

KraftHeinz - New Ulm - Plant 8302
 2525 S BRIDGE STREET
 NEW ULM, MN
 US 56073
 Contact: RYAN SCHMID
 ryan.schmid@kraftheinz.com
 T: (507)568-0338
 F: (507)354-7927

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)