




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
1122M
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0108849	GFL0105651	GFL0101562
Sample Date	Client Info	15 Jan 2024	07 Dec 2023	10 Nov 2023
Machine Age	hrs	12530	12266	12086
Oil Age	hrs	12266	12086	11616
Oil Changed	Client Info	Changed	Not Changd	N/A
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >3.0	<1.0	<1.0	0.2
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >200	19	17	12
Chromium	ppm ASTM D5185m >20	3	3	1
Nickel	ppm ASTM D5185m >2	0	0	<1
Titanium	ppm ASTM D5185m >2	<1	0	<1
Silver	ppm ASTM D5185m >2	0	0	<1
Aluminum	ppm ASTM D5185m >30	3	3	2
Lead	ppm ASTM D5185m >30	0	0	<1
Copper	ppm ASTM D5185m >30	12	12	16
Tin	ppm ASTM D5185m >15	<1	0	<1
Vanadium	ppm ASTM D5185m	<1	0	<1
Cadmium	ppm ASTM D5185m	0	0	<1

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	37	54	70
Barium	ppm ASTM D5185m 0	2	0	1
Molybdenum	ppm ASTM D5185m 60	41	38	42
Manganese	ppm ASTM D5185m 0	2	2	2
Magnesium	ppm ASTM D5185m 1010	562	496	493
Calcium	ppm ASTM D5185m 1070	1523	1607	1606
Phosphorus	ppm ASTM D5185m 1150	953	782	935
Zinc	ppm ASTM D5185m 1270	1141	1080	1076
Sulfur	ppm ASTM D5185m 2060	2777	3077	3016

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >30	6	5	8
Sodium	ppm ASTM D5185m	7	6	2
Potassium	ppm ASTM D5185m >20	20	18	21

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	0.2	0.2	0.1
Nitration	Abs/cm *ASTM D7624 >20	6.6	5.8	5.0
Sulfation	Abs/.1mm *ASTM D7415 >30	22.6	22.4	22.3

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	20.5	20.1	19.5
Base Number (BN)	mg KOH/g ASTM D2896 9.8	10.1	9.0	10.5







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	12.9	12.8	12.8

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0108849 **Received** : 18 Jan 2024
Lab Number : **06064836** **Diagnosed** : 21 Jan 2024
Unique Number : 10836218 **Diagnostician** : Don Baldrige
Test Package : FLEET

GFL Environmental - 415 - Michigan East
 6200 Elmridge
 Sterling Heights, MI
 US 48313
 Contact: Frank Wolak
 fwolak@gflenv.com
 T: (586)825-9514
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)