


# **OIL ANALYSIS REPORT**

### Sample Rating Trend









Machine Id DT676 Component Transmission (Auto)

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the fluid.

## **Fluid Condition**


The condition of the fluid is acceptable for the time in service.

GNIS EMGARD 28	05 ATF ( QTS)		Nov202	2 Mar2023	Aug2023 Ja	n2024	
	SAMPLE INFOR	RMATION		limit/base	current	history1	history2
	Sample Number		Client Info		PCA0111632	PCA0101891	PCA009527
terval to monitor.	Sample Date		Client Info		09 Jan 2024	11 Aug 2023	22 Mar 2023
J <del></del>	Machine Age	mls	Client Info		0	0	0
re normal.	Oil Age	mls	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
contamination in the	Sample Status				NORMAL	NORMAL	NORMAL
	CONTAMINA	ΓΙΟΝ	method	limit/base	current	history1	history2
eptable for the time	Water		WC Method	>0.1	NEG	NEG	NEG
cceptable for the time	WEAR METAI	_S	method	limit/base	current	history1	history2
	Iron	ppm	ASTM D5185m	>220	71	55	42
	Chromium	ppm	ASTM D5185m		0	0	0
	Nickel	ppm	ASTM D5185m		0	0	0
	Titanium	ppm	ASTM D5185m	20	0	0	0
	Silver	ppm	ASTM D5185m	>5	0	0	0
	Aluminum	ppm	ASTM D5185m		24	16	14
	Lead	ppm	ASTM D5185m		62	50	38
			ASTM D5185m		41	33	28
	Copper	ppm				3	2
	Tin	ppm	ASTM D5185m	>10	4		
	Vanadium	ppm	ASTM D5185m		0	0	0
	Cadmium	ppm	ASTM D5185m		0	0	0
	ADDITIVES		method	limit/base		history1	history?
	Boron	ppm	ASTM D5185m		136	121	148
	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		6	6	6
	Manganese	ppm	ASTM D5185m		<1	1	<1
	Magnesium	ppm	ASTM D5185m		31	29	26
	Calcium	ppm	ASTM D5185m		243	237	231
	Phosphorus	ppm	ASTM D5185m		458	414	432
	Zinc	ppm	ASTM D5185m		113	104	104
	Sulfur	ppm	ASTM D5185m		2316	2528	2811
	CONTAMINA	NTS	method	limit/base	current	history1	history
	Silicon	ppm	ASTM D5185m	>25	7	6	5
	Sodium	ppm	ASTM D5185m		7	8	6
	Potassium	ppm	ASTM D5185m	>20	3	3	1
	VISUAL		method	limit/base	current	history1	history
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	_			NORML	NORML	NORML	NORML
	Appearance	scalar	*Visual				
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
	Free Water	scalar	*Visual		NEG	NEG	NEG

Submitted By: DAVID WEBB





# **OIL ANALYSIS REPORT**




FLUID PROPI	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	38.9	35.4	35.5	37.3
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

## **GRAPHS**









Certificate L2367

Laboratory Sample No. Lab Number

Unique Number : 10836616 Test Package : FLEET

: PCA0111632 : 06065234

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 18 Jan 2024

Diagnosed : 22 Jan 2024 Diagnostician : Sean Felton

NW WHITE & CO - BEAUFORT DIVISION

1491 YENMASSEE HIGHWAY VARNVILLE, SC US 29944

Contact: VINCENT BULLOCK

bullockvince514@gmail.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: NWWVAR [WUSCAR] 06065234 (Generated: 01/22/2024 13:36:47) Rev: 1

Submitted By: DAVID WEBB

F: