




OIL ANALYSIS REPORT

Sample Rating Trend



WEAR



Machine Id
912005
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- QTS)

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

The nickel level is abnormal. All other component wear rates are normal.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

| method | limit/base | current | history1 | history2 |
|---------------|-------------|--------------------|-------------|-------------|
| Sample Number | Client Info | GFL0106662 | GFL0086219 | GFL0072873 |
| Sample Date | Client Info | 08 Jan 2024 | 02 Aug 2023 | 31 Jan 2023 |
| Machine Age | hrs | 4613 | 0 | 3856 |
| Oil Age | hrs | 600 | 4349 | 882 |
| Oil Changed | Client Info | Changed | N/A | Changed |
| Sample Status | | ABNORMAL | SEVERE | NORMAL |

CONTAMINATION

| method | limit/base | current | history1 | history2 |
|--------|----------------|------------|----------|----------|
| Water | WC Method >0.2 | NEG | NEG | NEG |
| Glycol | WC Method | NEG | NEG | NEG |

WEAR METALS

| method | limit/base | current | history1 | history2 |
|----------|----------------------|--------------|----------|----------|
| Iron | ppm ASTM D5185m >120 | 29 | 61 | 8 |
| Chromium | ppm ASTM D5185m >20 | 1 | 6 | <1 |
| Nickel | ppm ASTM D5185m >5 | ▲ 11 | <1 | <1 |
| Titanium | ppm ASTM D5185m >2 | 0 | 0 | 0 |
| Silver | ppm ASTM D5185m >2 | 0 | <1 | 0 |
| Aluminum | ppm ASTM D5185m >20 | 2 | 32 | 0 |
| Lead | ppm ASTM D5185m >40 | <1 | <1 | 0 |
| Copper | ppm ASTM D5185m >330 | 15 | 3 | 2 |
| Tin | ppm ASTM D5185m >15 | <1 | <1 | <1 |
| Vanadium | ppm ASTM D5185m | <1 | 0 | 0 |
| Cadmium | ppm ASTM D5185m | 0 | 0 | 0 |

ADDITIVES

| method | limit/base | current | history1 | history2 |
|------------|----------------------|--------------|----------|----------|
| Boron | ppm ASTM D5185m 0 | 5 | 3 | 2 |
| Barium | ppm ASTM D5185m 0 | <1 | 0 | 0 |
| Molybdenum | ppm ASTM D5185m 60 | 56 | 54 | 59 |
| Manganese | ppm ASTM D5185m 0 | 2 | 1 | <1 |
| Magnesium | ppm ASTM D5185m 1010 | 879 | 628 | 905 |
| Calcium | ppm ASTM D5185m 1070 | 964 | 895 | 1069 |
| Phosphorus | ppm ASTM D5185m 1150 | 976 | 749 | 962 |
| Zinc | ppm ASTM D5185m 1270 | 1199 | 931 | 1189 |
| Sulfur | ppm ASTM D5185m 2060 | 2496 | 2143 | 2845 |

CONTAMINANTS

| method | limit/base | current | history1 | history2 |
|-----------|---------------------|------------|----------|----------|
| Silicon | ppm ASTM D5185m >25 | 4 | 7 | 3 |
| Sodium | ppm ASTM D5185m | 6 | 3 | 2 |
| Potassium | ppm ASTM D5185m >20 | 2 | 111 | 1 |
| Fuel | % ASTM D3524 >3.0 | 0.7 | 18.3 | <1.0 |

INFRA-RED





| method | limit/base | current | history1 | history2 |
|-----------|--------------------------|-------------|----------|----------|
| Soot % | % *ASTM D7844 >4 | 0.8 | 1 | 0.4 |
| Nitration | Abs/cm *ASTM D7624 >20 | 9.8 | 9.3 | 7.4 |
| Sulfation | Abs/.1mm *ASTM D7415 >30 | 21.7 | 19.7 | 19.5 |

FLUID DEGRADATION

| method | limit/base | current | history1 | history2 |
|------------------|--------------------------|-------------|----------|----------|
| Oxidation | Abs/.1mm *ASTM D7414 >25 | 17.5 | 14.0 | 15.2 |
| Base Number (BN) | mg KOH/g ASTM D2896 9.8 | 5.6 | 5.5 | 7.5 |







OIL ANALYSIS REPORT



| VISUAL | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 | |
|------------------|--------|------------|---------|----------|----------|------|
| Visc @ 100°C | cSt | ASTM D445 | 15.4 | 13.7 | 7.9 | 13.9 |

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0106662 **Received** : 19 Jan 2024
Lab Number : 06065311 **Diagnosed** : 24 Jan 2024
Unique Number : 10836693 **Diagnostician** : Doug Bogart
Test Package : FLEET (Additional Tests: PercentFuel)

GFL Environmental - 405 - Arbor Hills
 7400 Napier Rd
 NORTHVILLE, MI
 US 48168
 Contact: John Nahal
 jnahal@gflenv.com
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)