


OIL ANALYSIS REPORT

OIL ANAL TOIC HEI OIL

(59083Z) Walgreens - Tractor [Walgreens - Tractor] 136A624219

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)



DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

The copper level is abnormal. In the absence of other significant wear metals, suspect copper due to sources other than wear (i.e. cooling core). All other metal levels are typical for a new component breaking in.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. No other contaminants were detected in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

| AL) | | | , | Jan 2024 | | |
|---------------|----------|-------------|------------|-------------|----------|----------|
| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | PCA0103573 | | |
| Sample Date | | Client Info | | 15 Jan 2024 | | |
| Machine Age | mls | Client Info | | 59720 | | |
| Oil Age | mls | Client Info | | 59720 | | |
| Oil Changed | | Client Info | | Changed | | |
| Sample Status | | | | ABNORMAL | | |
| CONTAMINATI | ON | method | limit/base | current | history1 | history2 |
| -uel | | WC Method | >5 | <1.0 | | |
| Nater | | WC Method | >0.2 | NEG | | |
| Glycol | | WC Method | | NEG | | |
| WEAR METALS | S | method | limit/base | current | history1 | history2 |
| ron | ppm | ASTM D5185m | >80 | 54 | | |
| Chromium | ppm | ASTM D5185m | >5 | 4 | | |
| Vickel | ppm | ASTM D5185m | >2 | <1 | | |
| Titanium | ppm | ASTM D5185m | | <1 | | |
| Silver | ppm | ASTM D5185m | >3 | <1 | | |
| Aluminum | ppm | ASTM D5185m | >30 | 94 | | |
| _ead | ppm | ASTM D5185m | >30 | 0 | | |
| Copper | ppm | ASTM D5185m | | <u> </u> | | |
| Γin | ppm | ASTM D5185m | >5 | 6 | | |
| /anadium | ppm | ASTM D5185m | | 0 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 2 | 15 | | |
| Barium | ppm | ASTM D5185m | 0 | 0 | | |
| Molybdenum | ppm | ASTM D5185m | 50 | 40 | | |
| Manganese | ppm | ASTM D5185m | | 5 | | |
| Magnesium | ppm | ASTM D5185m | 950 | 542 | | |
| Calcium | ppm | ASTM D5185m | 1050 | 1512 | | |
| Phosphorus | ppm | ASTM D5185m | 995 | 710 | | |
| Zinc | ppm | ASTM D5185m | 1180 | 821 | | |
| Sulfur | ppm | ASTM D5185m | 2600 | 1658 | | |
| CONTAMINAN | TS | method | limit/base | current | history1 | history2 |
| Silicon | ppm | | >20 | 8 | | |
| Sodium | ppm | ASTM D5185m | | 6 | | |
| Potassium | ppm | ASTM D5185m | >20 | 232 | | |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.7 | | |
| Vitration | Abs/cm | *ASTM D7624 | >20 | 11.8 | | |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 24.1 | | |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 27.9 | | |
| | | | | | | |



OIL ANALYSIS REPORT





* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (972)923-9928

F: (972)923-9919