


OIL ANALYSIS REPORT

(89533X) Walgreens - Tractor [Walgreens - Tractor] 136A66206

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| | | Арт | 2023 | Sep2023 Jan20; | 24 | |
|---------------|----------|-------------|------------|----------------|-------------|-------------|
| SAMPLE INFORM | ATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | PCA0105874 | PCA0105905 | PCA0091476 |
| Sample Date | | Client Info | | 04 Jan 2024 | 05 Sep 2023 | 28 Apr 2023 |
| Machine Age | mls | Client Info | | 656406 | 636825 | 611700 |
| Oil Age | mls | Client Info | | 50000 | 25125 | 50000 |
| Oil Changed | | Client Info | | Changed | Oil Added | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATIO | NC | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >110 | 14 | 10 | 14 |
| Chromium | ppm | ASTM D5185m | >4 | 0 | <1 | 0 |
| Nickel | ppm | ASTM D5185m | >2 | 0 | <1 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >25 | 3 | <1 | 5 |
| Lead | ppm | ASTM D5185m | >45 | 0 | <1 | 0 |
| Copper | ppm | ASTM D5185m | >85 | 3 | 4 | 9 |
| Tin | ppm | ASTM D5185m | >4 | 0 | <1 | 0 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 2 | 2 | 2 | 1 |
| Barium | ppm | ASTM D5185m | 0 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 50 | 59 | 61 | 64 |
| Manganese | ppm | ASTM D5185m | 0 | <1 | <1 | 0 |
| Magnesium | ppm | ASTM D5185m | 950 | 944 | 1011 | 1051 |
| Calcium | ppm | ASTM D5185m | 1050 | 999 | 1093 | 1215 |
| Phosphorus | ppm | ASTM D5185m | 995 | 959 | 1088 | 1092 |
| Zinc | ppm | ASTM D5185m | 1180 | 1226 | 1308 | 1360 |
| Sulfur | ppm | ASTM D5185m | 2600 | 2788 | 3800 | 3410 |
| CONTAMINANT | S | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >30 | 24 | 24 | 4 |
| Sodium | ppm | ASTM D5185m | | <1 | 2 | <1 |
| Potassium | ppm | ASTM D5185m | >20 | 1 | 3 | 5 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.5 | 0.4 | 0.6 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 9.3 | 8.2 | 9.7 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 20.2 | 17.9 | 21.2 |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 17.3 | 14.2 | 18.2 |
| | mg KOH/g | ASTM D2896 | | 7.3 | 8.5 | 6.9 |
| | 3 | | | | | |




OIL ANALYSIS REPORT





| VISUAL | | method | limit/base | current | history1 | history2 |
|-------------------------|--------|---------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| | | | | | | |


| FLUID PROPI | EHILO | method | | | riistory i | HISTORYZ |
|--------------|-------|-----------|-------|------|------------|----------|
| Visc @ 100°C | cSt | ASTM D445 | 12.00 | 11.7 | 11.9 | 11.3 |

GRAPHS











Certificate L2367

Laboratory Sample No.

Lab Number Unique Number : 10843985 Test Package : FLEET

: PCA0105874 : 06067308

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 22 Jan 2024

Diagnosed : 23 Jan 2024 Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Transervice - Shop 1361 - Berkeley-Windsor

4400 State Road 19 Windsor, WI US 53598

Contact: Mike Hurda mhurda@transervice.com T: (608)846-2726

F: (608)846-0389