


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL


Area
(A308899) {UNASSIGNED}
 Machine Id
2227
 Component
Diesel Engine
 Fluid
CHEVRON DELO 400 LE 15W40 (--- GAL)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0081087	PCA0081112	---
Sample Date	Client Info		15 Jan 2024	13 Feb 2023	---
Machine Age	mls	Client Info	61105	32232	---
Oil Age	mls	Client Info	32232	32232	---
Oil Changed	Client Info		Changed	Changed	---
Sample Status			NORMAL	ATTENTION	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	0.6	---
Water	WC Method	>0.2	NEG	NEG	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >165	36	76	---
Chromium	ppm	ASTM D5185m >5	2	5	---
Nickel	ppm	ASTM D5185m >4	<1	<1	---
Titanium	ppm	ASTM D5185m >2	0	0	---
Silver	ppm	ASTM D5185m >2	0	<1	---
Aluminum	ppm	ASTM D5185m >20	12	45	---
Lead	ppm	ASTM D5185m >150	2	5	---
Copper	ppm	ASTM D5185m >90	6	31	---
Tin	ppm	ASTM D5185m >5	<1	3	---
Vanadium	ppm	ASTM D5185m	<1	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	167	30	---
Barium	ppm	ASTM D5185m	0	5	---
Molybdenum	ppm	ASTM D5185m	104	20	---
Manganese	ppm	ASTM D5185m	1	7	---
Magnesium	ppm	ASTM D5185m	674	686	---
Calcium	ppm	ASTM D5185m	1389	1368	---
Phosphorus	ppm	ASTM D5185m 1200	682	661	---
Zinc	ppm	ASTM D5185m 1300	817	781	---
Sulfur	ppm	ASTM D5185m 3200	2333	3017	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >35	15	48	---
Sodium	ppm	ASTM D5185m	2	7	---
Potassium	ppm	ASTM D5185m >20	35	141	---



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >7.5	0.3	0.3	---
Nitration	Abs/cm	*ASTM D7624 >20	9.5	10.4	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	24.0	22.2	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	19.7	18.1	---
Base Number (BN)	mg KOH/g	ASTM D2896 9.6	6.7	5.7	---





OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.7	13.0	▲ 11.7

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0081087 **Received** : 22 Jan 2024
Lab Number : **06067580** **Diagnosed** : 23 Jan 2024
Unique Number : 10844257 **Diagnostician** : Wes Davis
Test Package : FLEET

Ergon Trucking Inc. - PET108
 929 US Highway 11 North
 Petal, MS
 US 39465
 Contact: Earlo Duck
 earlo.duck@ergon.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: