




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
[0098515]
 Machine Id
12073C

Component
Natural Gas Engine
 Fluid

PETRO CANADA DURON GEO LD 15W40 (8 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: E Service)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2	
Sample Number	Client Info	GFL0098515	GFL0087796	GFL0069213	
Sample Date	Client Info	24 Jan 2024	17 Jul 2023	27 Jan 2023	
Machine Age	hrs	Client Info	7545	6817	6460
Oil Age	hrs	Client Info	1085	357	513
Oil Changed	Client Info	Changed	Not Changd	Changed	
Sample Status		NORMAL	NORMAL	NORMAL	

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.1	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >50	12	12	13
Chromium	ppm ASTM D5185m >4	<1	<1	1
Nickel	ppm ASTM D5185m >2	<1	0	<1
Titanium	ppm ASTM D5185m	0	0	0
Silver	ppm ASTM D5185m >3	0	0	0
Aluminum	ppm ASTM D5185m >9	2	1	2
Lead	ppm ASTM D5185m >30	12	0	2
Copper	ppm ASTM D5185m >35	1	<1	1
Tin	ppm ASTM D5185m >4	<1	0	<1
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 50	12	25	8
Barium	ppm ASTM D5185m 5	0	0	0
Molybdenum	ppm ASTM D5185m 50	57	59	56
Manganese	ppm ASTM D5185m 0	<1	<1	<1
Magnesium	ppm ASTM D5185m 560	600	616	571
Calcium	ppm ASTM D5185m 1510	1711	1789	1691
Phosphorus	ppm ASTM D5185m 780	774	820	674
Zinc	ppm ASTM D5185m 870	1038	1058	988
Sulfur	ppm ASTM D5185m 2040	2343	3112	2767

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >+100	4	4	4
Sodium	ppm ASTM D5185m	5	6	5
Potassium	ppm ASTM D5185m >20	2	0	0

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844	0	0	0.1
Nitration	Abs/cm *ASTM D7624 >20	12.0	10.0	12.1
Sulfation	Abs/.1mm *ASTM D7415 >30	24.5	19.8	24.3

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	19.3	16.7	19.3
Base Number (BN)	mg KOH/g ASTM D2896 10.2	4.5	6.2	3.8







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.1	14.4	14.5	14.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0098515 **Received** : 25 Jan 2024
Lab Number : **06070210** **Diagnosed** : 26 Jan 2024
Unique Number : 10846887 **Diagnostician** : Don Baldrige
Test Package : FLEET

GFL Environmental - 006 - Wilmington
 3618 US Highway 421 N
 Wilmington, NC
 US 28401
 Contact: Eric Wood
 eric.wood@gflenv.com
 T: (717)723-1956
 F: (910)762-6880

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)