




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
(GFU934) {unassigned}
Machine Id
934026
Component
Natural Gas Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)



DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0066899	---	---
Sample Date	Client Info		24 Jan 2024	---	---
Machine Age	hrs	Client Info	1152	---	---
Oil Age	hrs	Client Info	1152	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			NORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.1	NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	92	---	---
Chromium	ppm	ASTM D5185m >4	2	---	---
Nickel	ppm	ASTM D5185m >2	2	---	---
Titanium	ppm	ASTM D5185m	<1	---	---
Silver	ppm	ASTM D5185m >3	0	---	---
Aluminum	ppm	ASTM D5185m >9	25	---	---
Lead	ppm	ASTM D5185m >30	4	---	---
Copper	ppm	ASTM D5185m >35	22	---	---
Tin	ppm	ASTM D5185m >4	3	---	---
Vanadium	ppm	ASTM D5185m	0	---	---
Cadmium	ppm	ASTM D5185m	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	2	---	---
Barium	ppm	ASTM D5185m 0	4	---	---
Molybdenum	ppm	ASTM D5185m 60	64	---	---
Manganese	ppm	ASTM D5185m 0	17	---	---
Magnesium	ppm	ASTM D5185m 1010	922	---	---
Calcium	ppm	ASTM D5185m 1070	1317	---	---
Phosphorus	ppm	ASTM D5185m 1150	814	---	---
Zinc	ppm	ASTM D5185m 1270	1060	---	---
Sulfur	ppm	ASTM D5185m 2060	2406	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >+100	35	---	---
Sodium	ppm	ASTM D5185m	8	---	---
Potassium	ppm	ASTM D5185m >20	76	---	---

INFRA-RED


	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0	---	---
Nitration	Abs/cm	*ASTM D7624 >20	14.6	---	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	27.7	---	---

FLUID DEGRADATION


	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	27.3	---	---
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	3.4	---	---



OIL ANALYSIS REPORT








PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.1	NEG	---
Free Water	scalar	*Visual		NEG	---



FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	---

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0066899 **Recieved** : 26 Jan 2024
Lab Number : 06072111 **Diagnosed** : 30 Jan 2024
Unique Number : 10848788 **Diagnostician** : Jonathan Hester
Test Package : FLEET

GFL Environmental - 095 - Atlanta West
 2699 Cochran Industrial Blvd
 Douglasville, GA
 US 30127-1332
 Contact: Darrell Welch
 darrell.welch@gflenv.com
 T: (800)207-6618
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)