

OIL ANALYSIS REPORT

(AY413B) Supermarket - Tractor FREIGHTLINER 107A8811

Component Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Fluid

Metal levels are typical for a new component breaking in.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)		Ma	y2023	Sep2023 Jan20	24	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0111023	PCA0104094	PCA0097068
Sample Date		Client Info		13 Jan 2024	20 Sep 2023	20 May 2023
Machine Age	mls	Client Info		61165	44809	32574
Oil Age	mls	Client Info		16356	11235	24464
Oil Changed		Client Info		Changed	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	29	52	29
Chromium	ppm	ASTM D5185m	>5	2	3	2
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	<1	<1
Aluminum	ppm	ASTM D5185m	>30	20	36	17
Lead	ppm	ASTM D5185m	>30	<1	0	1
Copper	ppm	ASTM D5185m	>150	95	149	324
Tin	ppm	ASTM D5185m	>5	<1	2	2
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	19	15	20
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	64	66	61
Manganese	ppm	ASTM D5185m	0	<1	2	2
Magnesium	ppm	ASTM D5185m	950	877	912	847
Calcium	ppm	ASTM D5185m	1050	1215	1435	1290
Phosphorus	ppm	ASTM D5185m	995	996	982	941
Zinc	ppm	ASTM D5185m	1180	1207	1250	1174
Sulfur	ppm	ASTM D5185m	2600	2473	2642	2953
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	5	8	6
Sodium	ppm	ASTM D5185m		2	3	3
Potassium	ppm	ASTM D5185m		57	97	46
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.8	1	0.6
Nitration	Abs/cm	*ASTM D7624		8.4	10.4	9.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.8	23.0	20.2
FLUID DEGRA		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.8	20.6	16.5
Base Number (BN)	mg KOH/g	ASTM D2896		7.4	6.5	8.3


Sample Rating Trend

NORMAL



OIL ANALYSIS REPORT

VISUAL



	Laboratory Sample No. Lab Number Unique Number	: WearCheck USA - : PCA0111023 : 06072505 : 10849182	501 Madia Recieved Diagnose Diagnost	d : 29 . ed : 30 .	ry, NC 27513 Ian 2024 Ian 2024 5 Davis	Transervic	e - Shop 1071 - Su 60	upermarket-Dayto A Tower Roa Dayton, N US 0881
		8 Abnormal 8 C 2/02/eW	Sep 20/23		88 2.0. 1.0. +7/21/21	May20/23	Sep20/23 -	2001
		11- 10-			(6,7.0 6.0 6.0 9 10 9 10 9 10 9 10 10 10 10 10 10 10 10 10 10 10 10 10			
	2	14 Abnormal 13 - 5 12 Base			8.0· (6,7.0· HO G.0·		<u> </u>	
		Viscosity @ 100°			9.0-	Base Number		
		May20/23	Sep 20/23		Jan13/24			
		100 - 50 -						
	ud.	250 200 150						
		300 - copper lead						
		Non-ferrous Met	als		Jan 13/24			
			23	584	24			
	ä	20-			/			
Sep20/23		50 - chromium nickel	\wedge					
		GRAPHS Ferrous Alloys						
		Visc @ 100°C	cSt	ASTM D445	12.00	11.4	11.0	11.0
		Free Water	scalar ERTIES	*Visual method	limit/base	NEG current	NEG history1	NEG history2
.,		Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Sep20/23	Jan 13/24 -	Appearance Odor	scalar scalar	*Visual *Visual	NORML NORML	NORML NORML	NORML NORML	NORML NORML
		Debris Sand/Dirt	scalar scalar	*Visual *Visual	NONE NONE	NONE NONE	NONE NONE	NONE
		Silt	scalar	*Visual	NONE	NONE	NONE	NONE
		Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE

1

Ĭ.