


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
DT814
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 10W30 (36 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0113165	PCA0096937	---
Sample Date	Client Info		22 Jan 2024	02 Jun 2023	---
Machine Age	mls	Client Info	55865	27798	---
Oil Age	mls	Client Info	28067	0	---
Oil Changed	Client Info		Changed	Changed	---
Sample Status			NORMAL	NORMAL	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	---
Water	WC Method	>0.2	NEG	NEG	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	34	47	---
Chromium	ppm	ASTM D5185m >20	2	2	---
Nickel	ppm	ASTM D5185m >5	6	3	---
Titanium	ppm	ASTM D5185m >2	0	<1	---
Silver	ppm	ASTM D5185m >2	<1	<1	---
Aluminum	ppm	ASTM D5185m >20	11	16	---
Lead	ppm	ASTM D5185m >40	<1	<1	---
Copper	ppm	ASTM D5185m >330	46	110	---
Tin	ppm	ASTM D5185m >15	2	5	---
Vanadium	ppm	ASTM D5185m	0	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	3	64	---
Barium	ppm	ASTM D5185m 0	0	0	---
Molybdenum	ppm	ASTM D5185m 50	65	116	---
Manganese	ppm	ASTM D5185m 0	2	6	---
Magnesium	ppm	ASTM D5185m 950	877	792	---
Calcium	ppm	ASTM D5185m 1050	1088	1460	---
Phosphorus	ppm	ASTM D5185m 995	923	756	---
Zinc	ppm	ASTM D5185m 1180	1172	936	---
Sulfur	ppm	ASTM D5185m 2600	2252	2620	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	14	73	---
Sodium	ppm	ASTM D5185m	7	4	---
Potassium	ppm	ASTM D5185m >20	32	51	---



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	0.7	0.5	---
Nitration	Abs/cm	*ASTM D7624 >20	10.6	12.1	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	23.0	23.6	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	20.1	23.3	---
Base Number (BN)	mg KOH/g	ASTM D2896	4.1	6.2	---





OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	10.9	10.17

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0113165 **Received** : 29 Jan 2024
Lab Number : 06072588 **Diagnosed** : 30 Jan 2024
Unique Number : 10849265 **Diagnostician** : Wes Davis
Test Package : FLEET

NW WHITE & CO - ANDERSON DIVISION
 2605 RIVER RD
 PIEDMONT, SC
 US 29673
 Contact: James Threatt
 jthreatt@nwwhite.com
 T: (864)918-4646
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)