OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
CHICAGO 95TH
Machine Id
TAYLOR T520M 452-11 (S/N S ED 34772)
Component
Diesel Engine
Fluid
NAPA Motor Oil 15W40 (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0105671**	PCA0097294	PCA0097286
Sample Date		Client Info		**06 Sep 2023**	11 Jul 2023	23 Jun 2023
Machine Age	hrs	Client Info		**14390**	0	14252
Oil Age	hrs	Client Info		**500**	0	250
Oil Changed		Client Info		**N/A**	Changed	Changed
Sample Status				**NORMAL**	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	**<1.0**	<1.0	<1.0
Water		WC Method	>0.2	**NEG**	NEG	NEG
Glycol		WC Method		**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>90	**5**	9	9
Chromium	ppm	ASTM D5185m	>20	**<1**	<1	<1
Nickel	ppm	ASTM D5185m	>2	**<1**	<1	<1
Titanium	ppm	ASTM D5185m	>2	**1**	2	2
Silver	ppm	ASTM D5185m	>2	**0**	0	0
Aluminum	ppm	ASTM D5185m	>20	**<1**	<1	<1
Lead	ppm	ASTM D5185m	>40	**2**	2	2
Copper	ppm	ASTM D5185m	>330	**3**	<1	<1
Tin	ppm	ASTM D5185m	>15	**<1**	<1	<1
Vanadium	ppm	ASTM D5185m		**<1**	<1	<1
Cadmium	ppm	ASTM D5185m		**0**	<1	<1

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**8**	5	4
Barium	ppm	ASTM D5185m		**0**	0	0
Molybdenum	ppm	ASTM D5185m		**48**	44	46
Manganese	ppm	ASTM D5185m		**<1**	<1	<1
Magnesium	ppm	ASTM D5185m		**804**	730	790
Calcium	ppm	ASTM D5185m		**1012**	1069	1179
Phosphorus	ppm	ASTM D5185m		**941**	884	965
Zinc	ppm	ASTM D5185m		**1110**	1088	1190
Sulfur	ppm	ASTM D5185m		**2679**	3265	3570

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	**3**	3	3
Sodium	ppm	ASTM D5185m		**4**	4	2
Potassium	ppm	ASTM D5185m	>20	**1**	12	4

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>6	**0.5**	0.4	0.5
Nitration	Abs/cm	*ASTM D7624	>20	**6.0**	5.4	5.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	**18.5**	17.9	18.1

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	**13.8**	12.9	13.2
Base Number (BN)	mg KOH/g	ASTM D2896		**9.5**	9.2	9.2

OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445		**14.1**	14.0	13.9

GRAPHS

















Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0105671
Lab Number : 06076510
Unique Number : 10858601
Test Package : MOB 1 (Additional Tests: TBN)

Received : 01 Feb 2024
Tested : 01 Feb 2024
Diagnosed : 01 Feb 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

NORTH AMERICAN STEVEDORING CO
9301 S KREITER AVE
CHICAGO, IL
US 60617
Contact: PACO MARTINEZ
paco.martinez@qsl.com
T:
F: