

OIL ANALYSIS REPORT

Sample Rating Trend

SAMPLE INFORMATION method limit/base



Fed224



Machine Id **733021** Component **Transmission (Auto)** Fluid **{not provided} (--- GAL)**

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.

Fluid Condition

The condition of the fluid is acceptable for the time in service.

Sample Number		Client Info		GFL0092120		
Sample Date		Client Info		01 Feb 2024		
Machine Age	hrs	Client Info		2475		
Oil Age	hrs	Client Info		2158		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ON	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>230	43		
Chromium	ppm	ASTM D5185m	>2	0		
Nickel	ppm	ASTM D5185m	>5	<1		
Titanium	ppm	ASTM D5185m	>2	0		
Silver	ppm	ASTM D5185m	>5	0		
Aluminum	ppm	ASTM D5185m	>65	10		
Lead	ppm	ASTM D5185m	>55	10		
Copper	ppm	ASTM D5185m	>85	6		
Tin	ppm	ASTM D5185m	>5	1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		99		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		14		
Phosphorus	ppm	ASTM D5185m		260		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		1290		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	5		
Sodium	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	4		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		

Contact/Location: See GFL856,GFL859 - Jose Gonzalez - GFL856



OIL ANALYSIS REPORT

FLUID PROPERTIES method limit/base



	Visc @ 40°C	cSt	ASTM D445		34.8		
	SAMPLE IMA	AGES	method	limit/base	current	history1	history2
67	Color				no image	no image	no image
Feb1/2	Bottom			_	no image	no image	no image
	GRAPHS						
	Ferrous Alloys						
	40 - iron chromium						
	35 nickel						
5	25						
1	20						
	10						
	5						
	-eb1/24			eb1/24			
	™ Non-ferrous Me	tals		ι.			
	10 9 copper						
	8 - tin						
	6						
	E 5						
	3						
	1-						
	01/24			b1/24 +			
	.≞ Viscosity @ 40º	c		B.			
	40- Abnormal						
	38						
_	36						
(J=UV) +0	2 34						
	30						
	28 - Abnormal						
	26						
	Feb 1/7			Feb1/2			
ratory ple No. Number Je Number Package	: WearCheck USA : GFL0092120 : 06079384 : 10861475 : FLEET	- 501 Mad Recieve Diagnos Diagnos	lison Ave., Car ed : 02 F sed : 05 F stician : Wes	y, NC 27513 eb 2024 eb 2024 Davis	GFL En	vironmental - 856 8515 Hi Contact:	- Houston Sout ghway 6 Sout Houston, T US 7708 Jose Gonzale
sample report, o	contact Customer Se	ervice at 1-	800-237-1369	tation		jgonzalez	22@gflenv.con
st methods that an conformity to speci	re outside of the ISC fications are based o) 17025 SC n the simpl	ope of accredi e acceptance d	ation. ecision rule (.	ICGM 106:2012	2)	T: E:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: See GFL856,GFL859 - Jose Gonzalez - GFL856