

OIL ANALYSIS REPORT

Area (51449Z) Walgreens - Tractor Machine Id [Walgreens - Tractor] 136A63380

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


63380						Ň
AL)			Aug2023	Feb2024		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0103639	PCA0099941	
Sample Date		Client Info		01 Feb 2024	17 Aug 2023	
Machine Age	mls	Client Info		153550	93328	
Oil Age	mls	Client Info		153550	50000	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	39	52	
Chromium	ppm	ASTM D5185m	>5	3	6	
Nickel	ppm	ASTM D5185m	>2	1	<1	
Titanium	ppm	ASTM D5185m		<1	<1	
Silver	ppm	ASTM D5185m	>3	<1	0	
Aluminum	ppm	ASTM D5185m	>30	30	112	
Lead	ppm	ASTM D5185m	>30	<1	0	
Copper	ppm	ASTM D5185m	>150	35	41	
Tin	ppm	ASTM D5185m	>5	1	2	
Vanadium	ppm	ASTM D5185m		0	<1	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	8	4	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	59	64	
Manganese	ppm	ASTM D5185m	0	1	2	
Magnesium	ppm	ASTM D5185m	950	943	982	
Calcium	ppm	ASTM D5185m	1050	1065	1265	
Phosphorus	ppm	ASTM D5185m	995	981	963	
Zinc	ppm	ASTM D5185m	1180	1224	1225	
Sulfur	ppm	ASTM D5185m	2600	2255	2508	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	6	6	
Sodium	ppm	ASTM D5185m		4	5	
Potassium	ppm	ASTM D5185m	>20	57	249	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1.1	0.9	
Nitration	Abs/cm	*ASTM D7624	>20	9.6	9.7	
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.1	20.9	
FLUID DEGRA		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.3	17.3	
Base Number (BN)	mg KOH/g	ASTM D2896		6.2	6.6	


Sample Rating Trend

NORMAL



OIL ANALYSIS REPORT





VISUAL NONE *Visual NONE NONE White Metal scalar Yellow Metal NONE NONE NONE scalar *Visual Precipitate scalar *Visual NONE NONE NONE Silt scalar *Visual NONE NONE NONE NONE Debris *Visual NONE NONE scalar Sand/Dirt NONE scalar *Visual NONE NONE NORML Appearance scalar *Visual NORML NORML Odor NORML NORML scalar *Visual NORML **Emulsified Water** scalar *Visual >0.2 NEG NEG Free Water scalar *Visual NEG NEG **FLUID PROPERTIES** Visc @ 100°C cSt ASTM D445 12.00 11.0 11.3 GRAPHS Ferrous Alloys 60 ar E 30 20 10 n Aug17/23 Feb1 Non-ferrous Metals 40 35 30 25 20

Feb 1/24

Feb1/24

: 05 Feb 2024

: 06 Feb 2024

7.

6. (B/HO) 5.0

E 4.0 e 3.0 器 2.0

> 1.0 0.0

> > Aug 17

Base Number



: Wes Davis Unique Number : 10862614 Diagnostician Test Package : FLEET Contact: Paul Santanella Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. psantanella@transervice.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Recieved

Diagnosed

15 10

15

14

13

Abnorma

: PCA0103639

: 06080523

Aug17/23 -

cSt (100°C)

Laboratory

Sample No.

Lab Number

Viscosity @ 100°C

Contact/Location: Paul Santanella - TSV1374

Transervice - Shop 1374 - Berkeley-Hartford

80 International Drive

T: (860)687-1037

F: (860)687-1476

Windsor, CT

US 06095

Feb1/24