


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **810041**

Component **Diesel Engine**

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

		un2022 Sep207	22 Dec2022 Feb2023 Ma			
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0107169	GFL0107259	GFL0088731
Sample Date		Client Info		05 Feb 2024	29 Dec 2023	30 Oct 2023
Machine Age	hrs	Client Info		18345	18093	17656
Oil Age	hrs	Client Info		153	599	160
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS	5	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	15	35	8
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	2	3	2
Lead	ppm	ASTM D5185m	>40	<1	0	1
Copper	ppm	ASTM D5185m	>330	7	43	6
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	3	8	10
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	60	62	55
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Madnesium	mag		1010		849	
Magnesium Calcium	ppm	ASTM D5185m		880 1024		806 939
Calcium	ppm	ASTM D5185m ASTM D5185m	1010 1070	880 1024	849 1026	806 939
Calcium Phosphorus	ppm	ASTM D5185m ASTM D5185m ASTM D5185m	1010 1070 1150	880 1024 977	849 1026 972	806 939 934
Calcium	ppm	ASTM D5185m ASTM D5185m	1010 1070	880 1024	849 1026	806 939
Calcium Phosphorus Zinc	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	1010 1070 1150 1270	880 1024 977 1205	849 1026 972 1146	806 939 934 1059
Calcium Phosphorus Zinc Sulfur CONTAMINANT	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method	1010 1070 1150 1270 2060 limit/base	880 1024 977 1205 2899	849 1026 972 1146 2565	806 939 934 1059 2576 history2
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D5185m	1010 1070 1150 1270 2060	880 1024 977 1205 2899 current	849 1026 972 1146 2565 history1	806 939 934 1059 2576 history2
Calcium Phosphorus Zinc Sulfur CONTAMINANT	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method	1010 1070 1150 1270 2060 limit/base	880 1024 977 1205 2899	849 1026 972 1146 2565 history1	806 939 934 1059 2576 history2
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon Sodium	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m Method ASTM D5185m ASTM D5185m	1010 1070 1150 1270 2060 limit/base >25	880 1024 977 1205 2899 current 6 22	849 1026 972 1146 2565 history1 9	806 939 934 1059 2576 history2 5
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon Sodium Potassium INFRA-RED	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m MEthod ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	1010 1070 1150 1270 2060 limit/base >25 >20	880 1024 977 1205 2899 current 6 22 6	849 1026 972 1146 2565 history1 9 45 9	806 939 934 1059 2576 history2 5 5 5
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon Sodium Potassium INFRA-RED Soot %	ppm	ASTM D5185m *ASTM D5185m	1010 1070 1150 1270 2060 limit/base >25 >20 limit/base	880 1024 977 1205 2899 current 6 22 6 current 0.6	849 1026 972 1146 2565 history1 9 45 9 history1 0.9	806 939 934 1059 2576 history2 5 5 5 5
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm ppm ppm ppm ppm ppm ppm Abs/cm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m Method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	1010 1070 1150 1270 2060 limit/base >25 >20 limit/base	880 1024 977 1205 2899 current 6 22 6 current 0.6 6.8	849 1026 972 1146 2565 history1 9 45 9 history1 0.9 9.5	806 939 934 1059 2576 history2 5 5 5 5 history2 0.3 6.3
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm ppm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m Method ASTM D5185m Method *ASTM D7844 *ASTM D7624 *ASTM D7415	1010 1070 1150 1270 2060 limit/base >25 >20 limit/base	880 1024 977 1205 2899 current 6 22 6 current 0.6 6.8 18.5	849 1026 972 1146 2565 history1 9 45 9 history1 0.9 9.5 20.0	806 939 934 1059 2576 history2 5 5 5 5 0.3 6.3 17.8
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation FLUID DEGRAD	ppm ppm ppm ppm ppm ppm ppm ppm Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m METHOD ASTM D5185m METHOD ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m METHOD *ASTM D7844 *ASTM D7624 *ASTM D7415 METHOD	1010 1070 1150 1270 2060 limit/base >25 >20 limit/base >3 >20 >30 limit/base	880 1024 977 1205 2899 current 6 22 6 current 0.6 6.8 18.5	849 1026 972 1146 2565 history1 9 45 9 history1 0.9 9.5 20.0 history1	806 939 934 1059 2576 history2 5 5 5 history2 0.3 6.3 17.8 history2
Calcium Phosphorus Zinc Sulfur CONTAMINANT Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm ppm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m Method ASTM D5185m Method *ASTM D7844 *ASTM D7624 *ASTM D7415	1010 1070 1150 1270 2060 limit/base >25 >20 limit/base >3 >20 >30	880 1024 977 1205 2899 current 6 22 6 current 0.6 6.8 18.5	849 1026 972 1146 2565 history1 9 45 9 history1 0.9 9.5 20.0	806 939 934 1059 2576 history2 5 5 5 5 0.3 6.3 17.8



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPI	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	12.7	12.9

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : FLEET

: GFL0107169 : 06081110

: 10863201

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 06 Feb 2024 Recieved Diagnosed : 06 Feb 2024

Diagnostician : Wes Davis

GFL Environmental - 010 - Stockbridge

1280 Rum Creek Parkway Stockbridge, GA US 30281

Contact: JOSHUA TINKER joshuatinker@gflenv.com

T:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: