OIL DIAGNOSTICS

OIL ANALYSIS REPORT

Sample Rating Trend

WEAR

Area
(69978Z) Walgreens - Tractor
Machine Id
[Walgreens - Tractor] 136A624309
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

The copper level is abnormal. In the absence of other significant wear metals, suspect copper due to sources other than wear (i.e. cooling core). All other component wear rates are normal.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0105893**	---	---
Sample Date		Client Info		**30 Jan 2024**	---	---
Machine Age	hrs	Client Info		**25482**	---	---
Oil Age	hrs	Client Info		**0**	---	---
Oil Changed		Client Info		**N/A**	---	---
Sample Status				**ABNORMAL**	---	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel		WC Method	>5	**<1.0**	---	---
Water		WC Method	>0.2	**NEG**	---	---
Glycol		WC Method		**NEG**	---	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	**47**	---	---
Chromium	ppm	ASTM D5185m	>5	**4**	---	---
Nickel	ppm	ASTM D5185m	>2	**2**	---	---
Titanium	ppm	ASTM D5185m		**<1**	---	---
Silver	ppm	ASTM D5185m	>3	**<1**	---	---
Aluminum	ppm	ASTM D5185m	>30	**45**	---	---
Lead	ppm	ASTM D5185m	>30	**<1**	---	---
Copper	ppm	ASTM D5185m	>150	▲ **198**	---	---
Tin	ppm	ASTM D5185m	>5	**4**	---	---
Vanadium	ppm	ASTM D5185m		**<1**	---	---
Cadmium	ppm	ASTM D5185m		**0**	---	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	**35**	---	---
Barium	ppm	ASTM D5185m	0	**0**	---	---
Molybdenum	ppm	ASTM D5185m	50	**41**	---	---
Manganese	ppm	ASTM D5185m	0	**4**	---	---
Magnesium	ppm	ASTM D5185m	950	**525**	---	---
Calcium	ppm	ASTM D5185m	1050	**1577**	---	---
Phosphorus	ppm	ASTM D5185m	995	**733**	---	---
Zinc	ppm	ASTM D5185m	1180	**891**	---	---
Sulfur	ppm	ASTM D5185m	2600	**2152**	---	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	**6**	---	---
Sodium	ppm	ASTM D5185m		**8**	---	---
Potassium	ppm	ASTM D5185m	>20	**120**	---	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	**0.4**	---	---
Nitration	Abs/cm	*ASTM D7624	>20	**9.2**	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	**23.4**	---	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	**21.5**	---	---
Base Number (BN)	mg KOH/g	ASTM D2896		**7.5**	---	---

OIL ANALYSIS REPORT

Aluminum (ppm)



Base Number



Viscosity @ 100°C



Aluminum (ppm)



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	---	---
Yellow Metal	scalar	*Visual	NONE	**NONE**	---	---
Precipitate	scalar	*Visual	NONE	**NONE**	---	---
Silt	scalar	*Visual	NONE	**NONE**	---	---
Debris	scalar	*Visual	NONE	**NONE**	---	---
Sand/Dirt	scalar	*Visual	NONE	**NONE**	---	---
Appearance	scalar	*Visual	NORML	**NORML**	---	---
Odor	scalar	*Visual	NORML	**NORML**	---	---
Emulsified Water	scalar	*Visual	>0.2	**NEG**	---	---
Free Water	scalar	*Visual		**NEG**	---	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	**9.7**	---	---

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0105893
Lab Number : 06081927
Unique Number : 10869372
Test Package : FLEET

Received : 06 Feb 2024
Tested : 07 Feb 2024
Diagnosed : 08 Feb 2024 - Sean Felton

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Transervice - Shop 1361 - Berkeley-Windsor
4400 State Road 19
Windsor, WI
US 53598
Contact: Mike Hurda
mhurda@transervice.com
T: (608)846-2726
F: (608)846-0389