




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(YA133455) [0111063]
 Machine Id
10639C
 Component
Natural Gas Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (36 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: E service)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0111063	GFL0087741	GFL0082232
Sample Date	Client Info	05 Feb 2024	01 Sep 2023	22 Jun 2023
Machine Age	hrs	18446	17152	16496
Oil Age	hrs	1294	2328	1672
Oil Changed	Client Info	Changed	Changed	Not Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.1	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >50	30	36	15
Chromium	ppm ASTM D5185m >4	4	5	2
Nickel	ppm ASTM D5185m >2	<1	1	<1
Titanium	ppm ASTM D5185m	0	<1	0
Silver	ppm ASTM D5185m >3	0	0	0
Aluminum	ppm ASTM D5185m >9	3	4	1
Lead	ppm ASTM D5185m >30	<1	3	<1
Copper	ppm ASTM D5185m >35	3	7	5
Tin	ppm ASTM D5185m >4	<1	<1	<1
Vanadium	ppm ASTM D5185m	0	<1	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 50	10	0	5
Barium	ppm ASTM D5185m 5	0	0	0
Molybdenum	ppm ASTM D5185m 50	56	64	58
Manganese	ppm ASTM D5185m 0	<1	1	<1
Magnesium	ppm ASTM D5185m 560	559	658	564
Calcium	ppm ASTM D5185m 1510	1475	1898	1672
Phosphorus	ppm ASTM D5185m 780	734	813	719
Zinc	ppm ASTM D5185m 870	940	1051	1034
Sulfur	ppm ASTM D5185m 2040	2252	2915	2766

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >+100	24	13	12
Sodium	ppm ASTM D5185m	10	34	16
Potassium	ppm ASTM D5185m >20	<1	0	2

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844	0	0.1	0.1
Nitration	Abs/cm *ASTM D7624 >20	11.5	13.5	10.7
Sulfation	Abs/.1mm *ASTM D7415 >30	22.6	27.8	22.0

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	19.0	24.6	19.3
Base Number (BN)	mg KOH/g ASTM D2896 10.2	4.3	2.5	3.8







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.1	14.7	14.2

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0111063
Lab Number : 06082382
Unique Number : 10869827
Test Package : FLEET

GFL Environmental - 006 - Wilmington
 3618 US Highway 421 N
 Wilmington, NC
 US 28401
 Contact: Eric Wood
 eric.wood@gflenv.com
 T: (717)723-1956
 F: (910)762-6880

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)