


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



DRYING [908193431] [DRYING] DB-13017 DB-13017 Component

Gearbox

PETRO CANADA PURITY FG SYNTH EP GEAR 220 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


LAIT LLO (GA	_,	far2013 Mar20	15 May2016 Aug2017 No	v2018 Feb2020 Mar2021 Jul2022	May2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0111066	PCA0078586	PCA0077242
Sample Date		Client Info		23 Jan 2024	11 May 2023	13 Oct 2022
Machine Age	hrs	Client Info		0	4201	4201
Oil Age	hrs	Client Info		4201	0	0
Oil Changed		Client Info		N/A	Not Changd	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
PQ		ASTM D8184		8	12	7
Iron	ppm	ASTM D5185m	>200	0	2	<1
Chromium	ppm	ASTM D5185m	>15	<1	0	0
Nickel	ppm	ASTM D5185m	>15	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	0	1
Lead	ppm	ASTM D5185m	>100	0	0	0
Copper	ppm	ASTM D5185m	>200	<1	0	<1
Tin	ppm	ASTM D5185m	>25	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		2	11	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		0	14	0
Calcium	ppm	ASTM D5185m		23	15	17
Phosphorus	ppm	ASTM D5185m		501	519	555
Zinc	ppm	ASTM D5185m		0	88	27
Sulfur	ppm	ASTM D5185m		463	559	607
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	4	5	6
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	0	<1	0
FLUID DEGRAI	OITAC	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.59	0.45	0.50	0.53



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG

FLUID PROP	ERIIES	method			riistory i	riistory
Visc @ 40°C	cSt	ASTM D445	221	202	200	200

SAMPLE IMAGES	













Color


Bottom







PQ

220









Certificate L2367

Laboratory Sample No. Lab Number : 06082685 Unique Number : 10870130

: PCA0111066

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** : 08 Feb 2024 - Wes Davis Diagnosed

: 07 Feb 2024

May11/23

: 08 Feb 2024

THE HERSHEY COMPANY WEST HERSHEY - TECHNICAL ASSURANCE, 1033 OLDE WEST CHOCOLATE HERSHEY, PA

US 17033 Contact: CLINTON ZOHNER

clintzohner@hersheys.com

Test Package : IND 2 (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (717)374-4846 F: (717)374-4594