




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
922014

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0069925	GFL0069914	GFL0059586
Sample Date	Client Info		19 Jan 2024	07 Dec 2023	09 Dec 2022
Machine Age	hrs	Client Info	458	319886	2370
Oil Age	hrs	Client Info	458	0	2370
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	SEVERE	SEVERE

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	0.12

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >110	6	20	55
Chromium	ppm	ASTM D5185m >4	<1	1	2
Nickel	ppm	ASTM D5185m >2	<1	1	<1
Titanium	ppm	ASTM D5185m	<1	0	<1
Silver	ppm	ASTM D5185m >2	0	0	<1
Aluminum	ppm	ASTM D5185m >25	1	6	7
Lead	ppm	ASTM D5185m >45	<1	4	110
Copper	ppm	ASTM D5185m >85	3	13	11
Tin	ppm	ASTM D5185m >4	1	<1	3
Vanadium	ppm	ASTM D5185m	<1	0	<1
Cadmium	ppm	ASTM D5185m	0	0	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	36	223	18
Barium	ppm	ASTM D5185m 0	<1	0	0
Molybdenum	ppm	ASTM D5185m 60	64	98	860
Manganese	ppm	ASTM D5185m 0	<1	2	1
Magnesium	ppm	ASTM D5185m 1010	876	673	319
Calcium	ppm	ASTM D5185m 1070	1071	1291	818
Phosphorus	ppm	ASTM D5185m 1150	954	712	320
Zinc	ppm	ASTM D5185m 1270	1121	831	357
Sulfur	ppm	ASTM D5185m 2060	2846	2482	2294

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >30	19	69	45
Sodium	ppm	ASTM D5185m	3	1	321
Potassium	ppm	ASTM D5185m >20	0	<1	550

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.2	0.4	1.2
Nitration	Abs/cm	*ASTM D7624 >20	6.0	8.3	14.1
Sulfation	Abs/.1mm	*ASTM D7415 >30	18.9	23.4	26.5

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	14.1	17.5	30.5
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	8.6	6.8	5.7







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.9	13.6

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0069925 **Received** : 08 Feb 2024
Lab Number : 06083269 **Tested** : 08 Feb 2024
Unique Number : 10870714 **Diagnosed** : 08 Feb 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 902 - Chilton HC
 428 High St
 Chilton, WI
 US 53014
 Contact: Keith Mueller
 keith.mueller@gflenv.com
 T: (920)374-1404
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)