

OIL ANALYSIS REPORT

Area (01KJ9A) Machine Id 723023-361636

Component Diesel Engine

Fluid PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



Sample Rating Trend





NORMAL

SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0109857	GFL0103337	GFL0099918
Sample Date		Client Info		06 Feb 2024	05 Jan 2024	15 Dec 2023
Machine Age	hrs	Client Info		25349	25185	25069
Oil Age	hrs	Client Info		0	600	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT		method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method	20.2	NEG	NEG	NEG
-	0		11 1. 0	-	-	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	13	1	18
Chromium	ppm	ASTM D5185m	>20	1	0	1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	1	2
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>330	1	<1	<1
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
ADDITIVES Boron	ppm	method ASTM D5185m	limit/base 0	current 10	history1 6	history2 33
	ppm ppm	ASTM D5185m				
Boron		ASTM D5185m	0	10	6	33
Boron Barium	ppm	ASTM D5185m ASTM D5185m	0 0 60	10 0	6 0	33 0
Boron Barium Molybdenum	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60	10 0 61	6 0 57	33 0 49
Boron Barium Molybdenum Manganese	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0	10 0 61 <1	6 0 57 <1	33 0 49 0
Boron Barium Molybdenum Manganese Magnesium	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010	10 0 61 <1 887	6 0 57 <1 923	33 0 49 0 565
Boron Barium Molybdenum Manganese Magnesium Calcium	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010 1070	10 0 61 <1 887 1166	6 0 57 <1 923 1071	33 0 49 0 565 1264
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010 1070 1150	10 0 61 <1 887 1166 984	6 0 57 <1 923 1071 1079	33 0 49 0 565 1264 725
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010 1070 1150 1270	10 0 61 <1 887 1166 984 1210	6 0 57 <1 923 1071 1079 1270	33 0 49 0 565 1264 725 930
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 1010 1070 1150 1270 2060	10 0 61 <1 887 1166 984 1210 3002	6 0 57 <1 923 1071 1079 1270 3129	33 0 49 0 565 1264 725 930 2352
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN	ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 1010 1070 1150 1270 2060	10 0 61 <1 887 1166 984 1210 3002 current	6 0 57 <1 923 1071 1079 1270 3129 history1	33 0 49 0 565 1264 725 930 2352 history2
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon	ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D5185m	0 0 60 1010 1070 1150 1270 2060 kimit/base >25	10 0 61 <1 887 1166 984 1210 3002 current 5	6 0 57 <1 923 1071 1079 1270 3129 history1 3	33 0 49 0 565 1264 725 930 2352 history2 5
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium	ppm ppm ppm ppm ppm ppm ppm TS	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 kimit/base	10 0 61 <1 887 1166 984 1210 3002 current 5 19	6 0 57 <1 923 1071 1079 1270 3129 history1 3 2	33 0 49 0 565 1264 725 930 2352 history2 5 29
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium	ppm ppm ppm ppm ppm ppm ppm TS	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 limit/base >25	10 0 61 <1 887 1166 984 1210 3002 current 5 19 2 2 current	6 0 57 <1 923 1071 1079 1270 3129 history1 3 2 2 2 history1	33 0 49 0 565 1264 725 930 2352 history2 5 29 2 2 history2
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED Soot %	ppm ppm ppm ppm ppm ppm ppm ppm TS ppm ppm	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 2060 225 >25 >20 limit/base >20	10 0 61 <1 887 1166 984 1210 3002 current 5 19 2 2 current 0.9	6 0 57 <1 923 1071 1079 1270 3129 history1 3 2 2 2 history1 0.2	33 0 49 0 565 1264 725 930 2352 history2 5 29 2 2 history2 1
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED	ppm ppm ppm ppm ppm ppm ppm TS ppm ppm	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 2060 225 >25 >20 limit/base >20	10 0 61 <1 887 1166 984 1210 3002 current 5 19 2 2 current	6 0 57 <1 923 1071 1079 1270 3129 history1 3 2 2 2 history1	33 0 49 0 565 1264 725 930 2352 history2 5 29 2 2 history2
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 <i>limit/base</i> >25 >20 <i>limit/base</i> >3 >20	10 0 61 <1 887 1166 984 1210 3002 <i>current</i> 5 19 2 <i>current</i> 0.9 7.2	6 0 57 <1 923 1071 1079 1270 3129 history1 3 2 2 history1 0.2 6.1	33 0 49 0 565 1264 725 930 2352 history2 5 29 2 2 history2 1 8.3
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm TS ppm ppm ppm ppm	ASTM D5185m ASTM D7844 *ASTM D7844 *ASTM D7844	0 0 0 1010 1070 1150 2260 225 220 220 imit/base >3 >20 >30 >30	10 0 61 <1 887 1166 984 1210 3002 current 5 19 2 current 0.9 7.2 20.1 current	6 0 57 <1 923 1071 1079 1270 3129 history1 3 2 2 history1 0.2 6.1 18.1 18.1	33 0 49 0 565 1264 725 930 2352 history2 5 29 2 2 history2 1 8.3 20.9 history2
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 /////////////////////////////////	10 0 61 <1 887 1166 984 1210 3002 <u>current</u> 5 19 2 2 <u>current</u> 0.9 7.2 20.1	6 0 57 <1 923 1071 1079 1270 3129 history1 3 2 2 2 history1 0.2 6.1 18.1	33 0 49 0 565 1264 725 930 2352 history2 5 29 2 2 history2 1 8.3 20.9




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.6	14.0	13.3
GRAPHS						

Ferrous Alloys



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: