

OIL ANALYSIS REPORT



Sample Rating Trend



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Metal levels are typical for a components first oil change.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

N SHP 15W40 (-	GAL)					
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0110135		
Sample Date		Client Info		06 Feb 2024		
Machine Age	hrs	Client Info		12825		
Oil Age	hrs	Client Info		12825		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2
-uel		WC Method	>3.0	<1.0		
Nater		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	_S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>200	2		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>2	0		
Γitanium	ppm	ASTM D5185m	>2	0		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>30	2		
_ead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>30	<1		
Гin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	42		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	60	63		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	1010	942		
Calcium	ppm	ASTM D5185m	1070	1080		
Phosphorus	ppm	ASTM D5185m	1150	1078		
Zinc	ppm	ASTM D5185m	1270	1266		
Sulfur	ppm	ASTM D5185m	2060	3247		
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	8		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	<1		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.1		
Nitration	Abs/cm	*ASTM D7624	>20	4.9		
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.3		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.6		
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.2		



OIL ANALYSIS REPORT




VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
ELLIID DRODE	DTIES	method	limit/base	current	hietory1	history2


FLUID PROPI	ERIIES	method			history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	


() 16 () 15 15 14

GRAPHS



¹⁰ T		copp	er i							
8 -	*********	••• lead	_}-							
6 -										
원 4-										
2 -										
0	eb6/24			 	 	 	 	 	 	-eb6/24









Laboratory Sample No.

: GFL0110135 Lab Number : 06085757

Unique Number : 10873202

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Tested

Diagnosed

: 12 Feb 2024 : 13 Feb 2024 : 13 Feb 2024 - Wes Davis

GFL Environmental - 468 - Dearborn 3051 Schaefer Rd Dearborn, MI US 48126 Contact:

Test Package : FLEET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: