




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
(BA85896)
Machine Id
772M
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (36 QTS)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0110066	GFL0104132	GFL0059283
Sample Date	Client Info		08 Feb 2024	04 Dec 2023	16 Nov 2023
Machine Age	hrs	Client Info	10634	10495	10482
Oil Age	hrs	Client Info	10634	10495	10482
Oil Changed	Client Info		Not Chngd	N/A	Not Chngd
Sample Status			NORMAL	NORMAL	ABNORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >75	10	27	28
Chromium	ppm	ASTM D5185m >5	<1	2	1
Nickel	ppm	ASTM D5185m >4	0	<1	▲ 6
Titanium	ppm	ASTM D5185m >2	0	<1	<1
Silver	ppm	ASTM D5185m >2	0	0	<1
Aluminum	ppm	ASTM D5185m >15	2	15	2
Lead	ppm	ASTM D5185m >25	0	<1	1
Copper	ppm	ASTM D5185m >100	<1	7	14
Tin	ppm	ASTM D5185m >4	0	2	2
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	11	67	2
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	61	73	63
Manganese	ppm	ASTM D5185m 0	<1	1	<1
Magnesium	ppm	ASTM D5185m 1010	923	529	1043
Calcium	ppm	ASTM D5185m 1070	1042	1985	1187
Phosphorus	ppm	ASTM D5185m 1150	1061	1177	1018
Zinc	ppm	ASTM D5185m 1270	1248	1380	1310
Sulfur	ppm	ASTM D5185m 2060	2860	4292	2386

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	4	14	8
Sodium	ppm	ASTM D5185m	76	0	5
Potassium	ppm	ASTM D5185m >20	0	48	0

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >6	0.2	0.3	0.9
Nitration	Abs/cm	*ASTM D7624 >20	7.9	6.5	9.2
Sulfation	Abs/.1mm	*ASTM D7415 >30	19.9	18.8	22.2

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	15.9	14.7	18.8
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	7.9	8.4	5.9







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.1	13.9	13.4

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0110066
Lab Number : 06085835
Unique Number : 10873280
Test Package : FLEET

Received : 12 Feb 2024
Tested : 13 Feb 2024
Diagnosed : 13 Feb 2024 - Wes Davis

GFL Environmental - 410 - Michigan West
 39000 Van Born Rd
 Wayne, MI
 US 48184

Contact: Belal Dgheish
 bdgheish@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (734)714-2340

F: