




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Area  
**(YA021452)**

Machine Id  
**2393**

Component  
**Diesel Engine**

Fluid  
**PETRO CANADA DURON SHP 15W40 (8 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>GFL0099834</b>	GFL0080522	GFL0080562
Sample Date	Client Info		<b>11 Feb 2024</b>	17 Oct 2023	04 Oct 2023
Machine Age	hrs	Client Info	<b>28719</b>	24658	24658
Oil Age	hrs	Client Info	<b>1200</b>	24658	24658
Oil Changed	Client Info		<b>Not Chngd</b>	Changed	Changed
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method		<b>NEG</b>	NEG	NEG

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >75	<b>85</b>	56	41
Chromium	ppm	ASTM D5185m >5	<b>5</b>	4	3
Nickel	ppm	ASTM D5185m >4	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m >2	<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m >2	<b>0</b>	<1	<1
Aluminum	ppm	ASTM D5185m >15	<b>3</b>	4	2
Lead	ppm	ASTM D5185m >25	<b>4</b>	<1	0
Copper	ppm	ASTM D5185m >100	<b>3</b>	3	2
Tin	ppm	ASTM D5185m >4	<b>&lt;1</b>	<1	<1
Vanadium	ppm	ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>3</b>	5	4
Barium	ppm	ASTM D5185m 0	<b>8</b>	<1	0
Molybdenum	ppm	ASTM D5185m 60	<b>71</b>	67	63
Manganese	ppm	ASTM D5185m 0	<b>0</b>	<1	<1
Magnesium	ppm	ASTM D5185m 1010	<b>1023</b>	1020	1015
Calcium	ppm	ASTM D5185m 1070	<b>1117</b>	1117	1124
Phosphorus	ppm	ASTM D5185m 1150	<b>966</b>	1122	1128
Zinc	ppm	ASTM D5185m 1270	<b>1313</b>	1373	1341
Sulfur	ppm	ASTM D5185m 2060	<b>3047</b>	3143	3222

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<b>15</b>	13	10
Sodium	ppm	ASTM D5185m	<b>2</b>	6	5
Potassium	ppm	ASTM D5185m >20	<b>2</b>	0	<1

## INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >6	<b>1.9</b>	1.6	1.4
Nitration	Abs/cm	*ASTM D7624 >20	<b>13.4</b>	11.1	10.2
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>26.5</b>	22.5	22.0

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>23.0</b>	18.5	17.6
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	<b>7.3</b>	7.8	8.7







# OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.3	14.0

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0099834 **Received** : 14 Feb 2024  
**Lab Number** : 06088553 **Tested** : 15 Feb 2024  
**Unique Number** : 10875998 **Diagnosed** : 15 Feb 2024 - Jonathan Hester  
**Test Package** : FLEET

**GFL Environmental - 018 - Fayetteville**  
 4621 Marracco Drive  
 Hope Mills, NC  
 US 28348  
 Contact: Robert Carter  
 robert.carter@gflenv.com  
 T: (910)596-1170  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)