


# **OIL ANALYSIS REPORT**



NORMAL



Machine Id **525089** 

Component **Diesel Engine** 

PETRO CANADA DURON SHP 15W40 (--- 0

# DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the


## **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

iAL)			Aug2023	Feb 2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0102758	GFL0090355	
Sample Date		Client Info		07 Feb 2024	25 Aug 2023	
Machine Age	hrs	Client Info		36556	35506	
Oil Age	hrs	Client Info		1050	35506	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	8	22	
Chromium	ppm	ASTM D5185m	>20	<1	2	
Nickel	ppm	ASTM D5185m	>4	0	0	
Titanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>20	2	4	
Lead	ppm	ASTM D5185m	>40	0	1	
Copper	ppm	ASTM D5185m	>330	2	2	
Tin	ppm	ASTM D5185m	>15	0	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	2	2	
Barium	ppm	ASTM D5185m	0	12	0	
Molybdenum	ppm	ASTM D5185m	60	49	57	
Manganese	ppm	ASTM D5185m	0	0	<1	
Magnesium	ppm	ASTM D5185m	1010	760	953	
Calcium	ppm	ASTM D5185m	1070	876	1132	
Phosphorus	ppm	ASTM D5185m	1150	895	1048	
Zinc	ppm	ASTM D5185m	1270	1009	1293	
Sulfur	ppm	ASTM D5185m	2060	2918	3904	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	7	
Sodium	ppm	ASTM D5185m		6	33	
Potassium	ppm	ASTM D5185m	>20	3	16	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.1	0.2	
Nitration	Abs/cm	*ASTM D7624	>20	5.2	7.7	
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.4	18.4	
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.2	14.5	
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	9.1	8.7	




# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROP	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.6	14.0	

## **GRAPHS**













Certificate L2367

Laboratory Sample No. Lab Number : 06088567

Unique Number : 10876012 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0102758 Received : 14 Feb 2024 Tested

: 15 Feb 2024 Diagnosed

: 15 Feb 2024 - Wes Davis

GFL Environmental - 963 - Peoria HC Disposal

1113 N. Swords Ave. West Peoria, IL US 61604

Contact: Corey Dozard cdozard@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: