


OIL ANALYSIS REPORT





PETRO CANADA HYDREX AW 46 (11 GAL)





DIAGNOSIS

Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

TEX AW 40 (III	GAL)		Jun2020	Feb 2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0065738	GFL0005818	
Sample Date		Client Info		09 Feb 2024	04 Jun 2020	
Machine Age	hrs	Client Info		0	4411	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		Not Changd	N/A	
Sample Status				ABNORMAL	ABNORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	2	8	
Chromium	ppm	ASTM D5185m	>10	0	2	
Nickel	ppm	ASTM D5185m	>4	<1	0	
Titanium	ppm	ASTM D5185m		0	<1	
Silver	ppm	ASTM D5185m		0	<1	
Aluminum	ppm	ASTM D5185m	>5	<1	<1	
Lead	ppm	ASTM D5185m	>4	0	<1	
Copper	ppm	ASTM D5185m	>15	0	2	
Tin	ppm	ASTM D5185m	>4	0	<1	
Antimony	ppm	ASTM D5185m			0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<1	19	
Barium	ppm	ASTM D5185m	0	0	<1	
Molybdenum	ppm	ASTM D5185m	0	1	8	
Manganese	ppm	ASTM D5185m	0	0	<1	
Magnesium	ppm	ASTM D5185m	0	25	45	
Calcium	ppm	ASTM D5185m	50	104	180	
Phosphorus	ppm	ASTM D5185m	330	359	342	
Zinc	ppm	ASTM D5185m	430	478	475	
Sulfur	ppm	ASTM D5185m	760	974	711	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	1	2	
Sodium	ppm	ASTM D5185m		<1	2	
Potassium	ppm	ASTM D5185m	>20	0	<1	
FLUID DEGRAI	DATION	method	limit/base	current	history1	history2



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	▲ MODER	▲ MODER	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46.4	46.2	45.2	
0.4451.5.144.6	. = .					

SAMPLE IMAGES Color no image **Bottom** no image


GRAPHS







Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)







Report Id: GFL823 [WUSCAR] 06088718 (Generated: 02/22/2024 19:02:50) Rev: 1

Laboratory Sample No. Lab Number : 06088718

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0065738

Unique Number : 10876163

Received **Tested** Diagnosed

: 14 Feb 2024 : 15 Feb 2024

: 15 Feb 2024 - Jonathan Hester

GFL Environmental - 823 - Central Missouri Hauling 24461 Oak Grove Lane Sedalia, MO

US 65301 Contact: Terry Randolph trandolph@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Test Package: FLEET (Additional Tests: PrtCount)

T: (660)631-2116