


OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id 193 Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- 0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QTS)						
SAMPLE INFOR	MATION	method	limit/base	Jan ² 024 Current	history1	history2
Sample Number		Client Info		PCA0114447		
Sample Date		Client Info		02 Jan 2024		
Machine Age	mls	Client Info		303452		
Oil Age	mls	Client Info		10200		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	30		
Chromium	ppm	ASTM D5185m	>20	2		
Nickel	ppm	ASTM D5185m	>4	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	<1		
Aluminum	ppm	ASTM D5185m	>20	1		
Lead	ppm	ASTM D5185m	>40	3		
Copper	ppm	ASTM D5185m	>330	1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	9		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	50	60		
Manganese	ppm	ASTM D5185m	0	<1		
Magnesium	ppm	ASTM D5185m	950	925		
Calcium	ppm	ASTM D5185m	1050	1075		
Phosphorus	ppm	ASTM D5185m	995	1037		
Zinc	ppm	ASTM D5185m	1180	1183		
Sulfur	ppm	ASTM D5185m	2600	3550		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	4		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5		
Nitration	Abs/cm	*ASTM D7624	>20	10.7		
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.4		
FLUID DEGRA	OITAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.3		
Base Number (BN)	mg KOH/g	ASTM D2896		6.8		




OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2	
White Metal	scalar	*Visual	NONE	NONE			
Yellow Metal	scalar	*Visual	NONE	NONE			
Precipitate	scalar	*Visual	NONE	NONE			
Silt	scalar	*Visual	NONE	NONE			
Debris	scalar	*Visual	NONE	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE			
Appearance	scalar	*Visual	NORML	NORML			
Odor	scalar	*Visual	NORML	NORML			
Emulsified Water	scalar	*Visual	>0.2	NEG			
Free Water	scalar	*Visual		NEG			
FILID PROPERTIES							


LLUID FUOF		memou			HISTOLAL	HISTOLYZ
Visc @ 100°C	cSt	ASTM D445	12.00	11.0		

GRAPHS



10 T	cop	per				
8 1	ead					
-	essesses till					
6						
4						
in the second			 	 	 	
2						
_			 	 	 	
0						
Jan2/24						200
n2						ç









Certificate L2367

Laboratory Sample No.

: PCA0114447 Lab Number : 06090826 Unique Number : 10883679 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

: 15 Feb 2024 Tested Diagnosed

: 19 Feb 2024 : 19 Feb 2024 - Wes Davis

US 16933 Contact: TARA MUIRHEAD tara.muirhead@gfsinc.net

GAS FIELD SPECIALISTS

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: GASMAN [WUSCAR] 06090826 (Generated: 02/19/2024 23:30:34) Rev: 1

Contact/Location: TARA MUIRHEAD - GASMAN

114 PA-660

T:

F:

MANSFIELD, PA