

Fuel

Iron

Silver

Lead

Tin

(TEMP) Walgreens - Yard Horse [Walgreens - Yard Horse] 136A81258 omponen

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.





SAMPLE INFORMATION method PCA0105872 PCA0105924 PCA0105936 Sample Number **Client Info** 08 Feb 2024 08 Jan 2024 07 Dec 2023 Sample Date Client Info 5550 Machine Age hrs **Client Info** 5550 5373 Oil Age hrs Client Info 200 200 211 Oil Changed Client Info Oil Added Oil Added Oil Added NORMAL Sample Status NORMAL NORMAL CONTAMINATION >5 WC Method <1.0 <1.0 <1.0 Water WC Method >0.2 NEG NEG NEG Glycol WC Method NEG NEG NEG WEAR METALS >100 24 14 18 ppm ASTM D5185m ASTM D5185m >20 2 Chromium ppm <1 <1 Nickel 1 2 ppm ASTM D5185m >4 <1 Titanium ppm ASTM D5185m <1 0 <1 ASTM D5185m >3 0 0 <1 ppm Aluminum >20 3 3 3 ppm ASTM D5185m 0 ASTM D5185m >40 <1 ppm <1 ASTM D5185m >330 Copper ppm 1 <1 <1 0 0 ppm ASTM D5185m >15 <1 Vanadium ppm ASTM D5185m <1 <1 <1 Cadmium 0 ASTM D5185m <1 ppm <1 ADDITIVES Boron ppm ASTM D5185m 2 1 0 2 Barium ASTM D5185m 0 0 0 0 ppm 52 Molvbdenum ASTM D5185m 50 54 59 ppm Manganese nnm AGTM DE185m O -1 0 -1

wanganese	ppm	ASTIVI DOTODITI	0	<1	0	< 1
Magnesium	ppm	ASTM D5185m	950	844	923	1106
Calcium	ppm	ASTM D5185m	1050	975	944	1150
Phosphorus	ppm	ASTM D5185m	995	972	990	1191
Zinc	ppm	ASTM D5185m	1180	1094	1206	1462
Sulfur	ppm	ASTM D5185m	2600	3426	2987	3594
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	3	4
Sodium	ppm	ASTM D5185m		0	1	4
Potassium	ppm	ASTM D5185m	>20	3	2	4
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.5	0.4
Nitration	Abs/cm	*ASTM D7624	>20	9.4	8.4	7.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.4	18.3	18.8
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1	15.0	14.9

7.2


Base Number (BN) mg KOH/g ASTM D2896


8.1

7.9





OIL ANALYSIS REPORT





VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	13.4	13.8	14.2
GRAPHS						





Certificate L2367

F: (608)846-0389