

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



911 (S/N 91800) Componen

Diesel Engine

PETRO CANADA DURON HP 15W40 (--- LT

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

·R)						
n)				Feb2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0044194		
Sample Date		Client Info		02 Feb 2024		
Machine Age	hrs	Client Info		844		
Oil Age	hrs	Client Info		344		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	45		
Chromium	ppm	ASTM D5185m	>20	1		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	<1		
Aluminum	ppm	ASTM D5185m	>20	7		
Lead	ppm	ASTM D5185m	>40	3		
Copper	ppm	ASTM D5185m	>330	117		
Tin	ppm	ASTM D5185m	>15	2		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		5		
Barium	ppm	ASTM D5185m		<1		
Molybdenum	ppm	ASTM D5185m		58		
Manganese	ppm	ASTM D5185m		2		
Magnesium	ppm	ASTM D5185m		910		
Calcium	ppm	ASTM D5185m		1022		
Phosphorus	ppm	ASTM D5185m		989		
Zinc	ppm	ASTM D5185m		1210		
Sulfur	ppm	ASTM D5185m		2825		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	22		
Sodium	ppm	ASTM D5185m		3		
Potassium	ppm	ASTM D5185m	>20	2		
Fuel	%	ASTM D3524	>5	0.5		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.1		
Nitration	Abs/cm	*ASTM D7624	>20	7.7		
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.1		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.6		
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	9.86		
(2.1.)				0.00		



OIL ANALYSIS REPORT







Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

: PCA0044194 Lab Number : 06091166 **Unique Number** : 10884019

Received **Tested** Diagnosed

: 19 Feb 2024 Test Package : MOB 2 (Additional Tests: FuelDilution, PercentFuel)

: 15 Feb 2024

: 19 Feb 2024 - Wes Davis

1767 GRIFFIN SHOULS RD DADEVILLE, AL

> Contact: RON INGRAM ron.ingram@ingrampaving.com T: (256)825-6878

GARY INGRAM GRADING & PAVING

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: GARDAD [WUSCAR] 06091166 (Generated: 02/23/2024 07:31:16) Rev: 1

Contact/Location: RON INGRAM - GARDAD

US 36853

F: