

OIL ANALYSIS REPORT

(P662031) 10892C

Component

Natural Gas Engine

PETRO CANADA DURON GEO LD 15W40 (11 GAL)

Sample Rating Trend



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


II GAL)		::2018 Jan2	020 Jul2020 Jan2021	Jul2021 Oct2021 May2022	Dec2023	
SAMPLE INFO	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0110378	GFL0096913	GFL0069746
Sample Date		Client Info		15 Feb 2024	07 Feb 2024	28 Dec 2023
Machine Age	hrs	Client Info		5650	5580	5270
Oil Age	hrs	Client Info		5650	5580	5270
Oil Changed		Client Info		Not Changd	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR META	LS	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>50	12	43	11
Chromium	ppm	ASTM D5185m	>4	1	4	<1
Nickel	ppm	ASTM D5185m	>2	1	2	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>9	3	4	2
Lead	ppm	ASTM D5185m	>30	1	7	3
Copper	ppm	ASTM D5185m	>35	1	2	<1
Tin	ppm	ASTM D5185m	>4	<1	1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	23	10	6
Barium	ppm	ASTM D5185m	5	0	2	0
Molybdenum	ppm	ASTM D5185m	50	83	73	63
Manganese	ppm	ASTM D5185m		1	2	<1
Vianganees	ppm	ASTM D5185m	560	898	749	678
Calcium	ppm	ASTM D5185m	1510	2156	1750	1668
Phosphorus	ppm	ASTM D5185m	780	1009	922	801
Zinc	ppm	ASTM D5185m	870	1437	1206	1096
Sulfur	ppm	ASTM D5185m	2040	3849	2595	2561
CONTAMINA		method	limit/base		history1	history2
				current		
Silicon	ppm	ASTM D5185m	>+100	9	43	8
Sodium Potassium	ppm	ASTM D5185m ASTM D5185m	>20	2	4	7
	ppm		•		•	
INFRA-RED		method	limit/base		history1	history2
Soot %	%	*ASTM D7844		0	0.1	0
Nitration	Abs/cm	*ASTM D7624		9.7	13.6	11.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	25.1	24.3
FLUID DEGRA	ADATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1	20.3	19.4
Dogs Number (DNI)	ma 1/011/a	ACTM DOOG	100	E O	6.3	2.4

Base Number (BN) mg KOH/g ASTM D2896 10.2 5.3



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	▲ MODER	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROP	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.1	14.2	13.6	14.1

GRAPHS













Certificate L2367

Laboratory Sample No.

Lab Number : 06092151 Unique Number : 10885004 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0110378 Received : 16 Feb 2024

Tested : 19 Feb 2024 Diagnosed : 20 Feb 2024 - Don Baldridge

GFL Environmental - 031 - Greenville/Spartanburg

1635 Antioch Church Rd Piedmont, SC US 29673

Contact: TECHNICIAN ACCOUNT catherine.anastasio@wearcheck.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: GFL031 [WUSCAR] 06092151 (Generated: 02/20/2024 16:17:59) Rev: 1

Submitted By: Matt Segars

T:

F: