


## **OIL ANALYSIS REPORT**

Sample Rating Trend



NORMAL



Machine Id

Component

**Natural Gas Engine** 

PETRO CANADA SENTRON LD 3000 (--- GAL)

### DIAGNOSIS

#### Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

#### Wear

All component wear rates are normal.

#### Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

#### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

AL)		Sep2023	0et2023	Nov2023 Jan2024	Feb 2024	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0117178	PCA0112029	PCA0103424
Sample Date		Client Info		01 Feb 2024	02 Jan 2024	01 Nov 2023
Machine Age	hrs	Client Info		146375	145653	144172
Oil Age	hrs	Client Info		3915	3193	1712
Oil Changed	1113	Client Info		Not Changd	Not Changd	Not Changd
Sample Status		Oliciti IIIIo		NORMAL	NORMAL	NORMAL
			11 1. 1			
CONTAMINATI	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	5	7	4
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	2	2	<1
Lead	ppm	ASTM D5185m	>30	<1	0	0
Copper	ppm	ASTM D5185m	>35	<1	<1	0
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	1	0	0	0
Molybdenum	ppm	ASTM D5185m	2	<1	2	0
Manganese	ppm	ASTM D5185m	1	<1	0	<1
Magnesium	ppm	ASTM D5185m	5	12	10	12
Calcium	ppm	ASTM D5185m	1220	1501	1516	1482
Phosphorus	ppm	ASTM D5185m	298	342	343	318
Zinc	ppm	ASTM D5185m	350	417	390	411
Sulfur	ppm	ASTM D5185m	1995	2634	2648	2585
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+100	2	2	2
Sodium	ppm	ASTM D5185m		2	0	0
Potassium	ppm	ASTM D5185m	>20	2	2	0
Fuel	%	ASTM D3524	>4.0	0.4	0.0	0.2
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	5.2	5.3	5.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.8	16.4	16.0
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.2	10.0	9.7
Acid Number (AN)		ASTM D8045		1.03	1.04	1.28
	901119	4.0TI.4.D0070	3.00		0.70	0.45

Base Number (BN) mg KOH/g ASTM D2896 3.9


3.29

2.76

3.45



# **OIL ANALYSIS REPORT**







Laboratory Sample No. Lab Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0117178

: 06092456 **Unique Number** : 10885309

Received **Tested** Diagnosed

: 20 Feb 2024 : 20 Feb 2024 - Wes Davis Test Package : MOB 2 ( Additional Tests: FuelDilution, PercentFuel )

: 16 Feb 2024

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

**ENERVEST OPERATING - HAYSI A** 

1242 WEST WIND ROAD

HAYSI, VA US 24256

Contact: CHARLES GREGORY cgregory@usacompression.com

T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: