


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



1004 Component

Diesel Engine

PETRO CANADA 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


		,		Feb 2024		
SAMPLE INFOR	RMATION	method				history2
Sample Number		Client Info		PCA0109914		
Sample Date		Client Info		12 Feb 2024		
Machine Age	hrs	Client Info		8607		
Oil Age	hrs	Client Info		500		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0		
Water		WC Method	7 0.0	NEG		
Glycol		WC Method	7 U.L	NEG		
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	91		
Chromium	ppm	ASTM D5185m	>20	1		
Nickel	ppm	ASTM D5185m	>5	2		
Titanium	ppm	ASTM D5185m	>2	4		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>20	10		
Lead	ppm	ASTM D5185m	>40	3		
Copper	ppm	ASTM D5185m	>330	11		
Tin	ppm	ASTM D5185m	>15	1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		4		
Barium	ppm	ASTM D5185m		10		
Molybdenum	ppm	ASTM D5185m		61		
Manganese	ppm	ASTM D5185m		3		
Magnesium	ppm	ASTM D5185m		908		
Calcium	ppm	ASTM D5185m		1049		
Phosphorus	ppm	ASTM D5185m		960		
Zinc	ppm	ASTM D5185m		1197		
Sulfur	ppm	ASTM D5185m		2627		
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	18		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	4		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	1		
Nitration	Abs/cm	*ASTM D7624	>20	11.5		
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.1		
FLUID DEGRA	DAT <u>ION</u>	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.1		
Door Number (DN)	7100/. IIIIIII	ACTM DOOG	<i>></i> 20	0.40		


6.19

Base Number (BN) mg KOH/g ASTM D2896



OIL ANALYSIS REPORT





Visc @ 100°C	cSt	ASTM D445	13.0
GRAPHS			
Iron (ppm) 300 250 250 200 Abnormal			Lead (ppm) 100 80 80 Abnormal 20 40 20 40 40 40 40 40 40 40 40 40 40 40 40 40
Aluminum (ppm) Severe Aluminum (ppm) Severe Aluminum (ppm) Severe Aluminum (ppm)			Chromium (ppm) 50 40 Severe Abnormal 10 42721 99 491777
Copper (ppm) Severe abnormal 300 100 77 77 122 138			Silicon (ppm) Severe Abnormal 4772149
Viscosity @ 100°(Base Number (mg KOH(g)) Base Number (mg KOH(g)) C C C C C C C C C C C C C C C C C C





Certificate L2367

Laboratory

Sample No.

Lab Number : 06093194 Unique Number : 10886047 Test Package : MOB 2

: PCA0109914

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

: 19 Feb 2024 : 20 Feb 2024 Diagnosed

: 20 Feb 2024 - Wes Davis

186 South Washington Street Norton, MA US 02766

Contact: Dave Wilson Jr. Dwilson1@win-waste.com

UMM - Shop 401 - Norton

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: