OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
744008
Component
Natural Gas Engine
Fluid
PETRO CANADA DURON GEO LD 15W40 (--- LTR)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**GFL0106998**	GFL0094239	GFL0085368
Sample Date		Client Info		**14 Feb 2024**	09 Nov 2023	04 Aug 2023
Machine Age	hrs	Client Info		**6368**	5879	5288
Oil Age	hrs	Client Info		**1080**	591	5288
Oil Changed		Client Info		**Changed**	Not Changd	Changed
Sample Status				**NORMAL**	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	**20**	5	13
Chromium	ppm	ASTM D5185m	>4	**0**	<1	2
Nickel	ppm	ASTM D5185m	>2	**0**	<1	<1
Titanium	ppm	ASTM D5185m		**0**	<1	<1
Silver	ppm	ASTM D5185m	>3	**0**	<1	<1
Aluminum	ppm	ASTM D5185m	>9	**<1**	2	2
Lead	ppm	ASTM D5185m	>30	**<1**	<1	2
Copper	ppm	ASTM D5185m	>35	**<1**	1	2
Tin	ppm	ASTM D5185m	>4	**<1**	<1	<1
Vanadium	ppm	ASTM D5185m		**0**	<1	<1
Cadmium	ppm	ASTM D5185m		**0**	<1	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	**2**	26	4
Barium	ppm	ASTM D5185m	5	**0**	0	0
Molybdenum	ppm	ASTM D5185m	50	**59**	51	57
Manganese	ppm	ASTM D5185m	0	**<1**	<1	<1
Magnesium	ppm	ASTM D5185m	560	**842**	556	607
Calcium	ppm	ASTM D5185m	1510	**1003**	1507	1798
Phosphorus	ppm	ASTM D5185m	780	**973**	799	747
Zinc	ppm	ASTM D5185m	870	**1142**	937	1052
Sulfur	ppm	ASTM D5185m	2040	**2852**	2576	3037

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+100	**3**	3	4
Sodium	ppm	ASTM D5185m		**19**	2	11
Potassium	ppm	ASTM D5185m	>20	**6**	3	6

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		**1.5**	0	0.1
Nitration	Abs/cm	*ASTM D7624	>20	**10.2**	8.4	9.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	**20.9**	18.8	21.1

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	**16.6**	16.2	17.1
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	**8.6**	8.0	4.9

OIL ANALYSIS REPORT

Base Number



Viscosity @ 100°C



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.1	**12.6**	14.6	14.7

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0106998
Lab Number : 06093974
Unique Number : 10886827
Test Package : FLEET

Received : 20 Feb 2024
Tested : 21 Feb 2024
Diagnosed : 21 Feb 2024 - Don Baldridge

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GFL Environmental - 882 - Gainesville
5002 SW 41st Blvd
Gainesville, FL
US 32608
Contact: ROBERT CLARK
robert.clark@gflenv.com
T:
F: