

OIL ANALYSIS REPORT

Area (TS45704) S0916A-Suamico Machine Id 523078 Component

Front Center Diesel Engine Fluid PETRO CANADA DURON SHP 15W40 (44 QT

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


_						
0						
QTS)		Jul	2023	Aug2023 Feb20	24	
SAMPLE INFOF	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0095948	GFL0074836	GFL0074830
Sample Date		Client Info		12 Feb 2024	16 Aug 2023	12 Jul 2023
Machine Age	hrs	Client Info		20579	20479	20473
Oil Age	hrs	Client Info		100	6	426
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	ΓΙΟΝ	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAI	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>165	16	7	35
Chromium	ppm	ASTM D5185m	>5	<1	<1	2
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	<1	<1	0
Aluminum	ppm	ASTM D5185m	>20	4	3	4
Lead	ppm	ASTM D5185m	>150	2	0	2
Copper	ppm	ASTM D5185m	>90	1	0	2
Tin	ppm	ASTM D5185m	>5	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	10	9	16
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	60	52	60
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	900	882	936
Calcium	ppm	ASTM D5185m	1070	1071	1063	1110
Phosphorus	ppm	ASTM D5185m	1150	1096	960	966
Zinc	ppm	ASTM D5185m	1270	1247	1177	1248
Sulfur	ppm	ASTM D5185m	2060	3180	3495	3463
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	6	4	6
Sodium	ppm	ASTM D5185m		4	1	4
Potassium	ppm	ASTM D5185m	>20	10	1	9
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>7.5	0.5	0.2	0.8
Nitration	Abs/cm	*ASTM D7624	>20	6.0	5.2	9.6
Sulfation	Abs/.1mm	*ASTM D7415		18.5	17.6	20.4
FLUID DEGRA		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.4	13.3	15.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	9.2	9.3	8.1

Sample Rating Trend

NORMAL



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Aug 16,23 Feb 12,24	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Feb 1	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
1	Free Water	scalar	*Visual		NEG	NEG	NEG
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2
	Visc @ 100°C	cSt	ASTM D445	15.4	14.1	14.3	14.0
	GRAPHS						
	Ferrous Alloys						
- (23 	30 - iron						
Aug 16/23	25-						
	E 15						
	10						
		-					
	5-						
	2	23		24			
	Jul12/23	Aug 16/23		Feb12/24			
	Non-ferrous Metal			ш.			
	¹⁰ T						
	copper						
	8 - where the time time the time time time time time time time tim						
	6-						
	ud d						
	4+						
	2 -			and the second			
			133340001340000000000000000000000000000				
		23		линания 1011			
		ug 16/23		eb12/24			
	Jul12/23	Aug16/23		Feb12/24			
		4		LL.	Base Numbe		
	Viscosity @ 100°C	4		LL.			
	Viscosity @ 100°C	4		10.0			
	Viscosity @ 100°C	4		10.0			
	Viscosity @ 100°C	4		10.0			
	Viscosity @ 100°C	4		10.0			
	Viscosity @ 100°C	4		(0)HOX BUD (0)HOX BUD			
	Viscosity @ 100°C	4		10.0			
	Viscosity @ 100°C			10.0- (0) 8.0- HOX Buy 6.0- unquint 4.0- 2.0- 0.0	Base		
	Viscosity @ 100°C			10.0- (0) 8.0- HOX Buy 6.0- unquint 4.0- 2.0- 0.0	Base		
	Viscosity @ 100°C	4		10.0 (6) (6) (6) (6) (6) (6) (6) (6) (6) (6)			
Laboratory	Viscosity @ 100°C	Aug16/23		10.0 (0,HOX 000) 10,0 (0,HOX 000) 10,0 (0,0)	Pase		116A - Suamio
Laboratory Sample No.	Viscosity @ 100°C	EZglg1Bhy 1 Madisc Rece	ived : 21	10.0 (0) HOX DE (0) HOX DE (0) HOX HOX HOX HOX HOX HOX HOX HOX HOX HOX	Pase	nvironmental - 9	Deerfield Ave
Laboratory Sample No. Lab Number	Viscosity @ 100°C	1 Madisc Rece Teste	ived : 21 ed : 27	10.0 (0,4) (0,	GFL E	nvironmental - 9	Deerfield Ave Suamico, V
Laboratory Sample No. Lab Number Unique Number	Viscosity @ 100°C	1 Madisc Rece Teste	ived : 21 ed : 27	10.0 (0) HOX DE (0) HOX DE (0) HOX HOX DE (0) HOX HOX HOX HOX HOX HOX HOX HOX	GFL E	nvironmental - 9 2300	1 16A - Suami o Deerfield Ave Suamico, N US 543
Laboratory Sample No. Lab Number	Viscosity @ 100°C	1 Madisc Rece Teste Diagi	ived : 21 ed : 27 nosed : 27	10.0 10.0	GFL E	nvironmental - 9 2300 Contact: NICHO	Deerfield Ave Suamico, \ US 543

Submitted By: Teresa Vuckovich Page 2 of 2