


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **322689**

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- 0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)		Ap	2023	Oct2023 Feb203	14	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0114576	PCA0105314	PCA0095720
Sample Date		Client Info		10 Feb 2024	05 Oct 2023	29 Apr 2023
Machine Age	mls	Client Info		8953	41012	28709
Oil Age	mls	Client Info		8953	41012	0
Oil Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	49	41	127
Chromium	ppm	ASTM D5185m	>20	1	1	3
Nickel	ppm	ASTM D5185m	>4	0	<1	2
Titanium	ppm	ASTM D5185m		1	1	1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m		10	9	17
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m		19	18	48
Tin Vanadium	ppm	ASTM D5185m ASTM D5185m	>15	0	3	6
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	ppm		limit/base			
		method		current	history1	history2
Boron	ppm	ASTM D5185m		8	9	24
Barium	ppm	ASTM D5185m		0	0	<1
Mongonoo	ppm	ASTM D5185m ASTM D5185m	50	50 2	57 2	46 9
Manganese Magnesium	ppm	ASTM D5185m	950	756	841	563
Calcium	ppm ppm	ASTM D5185m		1144	1247	1830
Phosphorus	ppm	ASTM D5185m	995	761	941	799
Zinc	ppm	ASTM D5185m	1180	991	1179	993
Sulfur	ppm	ASTM D5185m	2600	2291	3206	2542
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	5	12
Sodium	ppm	ASTM D5185m		1	3	8
Potassium	ppm	ASTM D5185m	>20	10	13	27
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.9	0.6	1.1
Nitration	Abs/cm	*ASTM D7624	>20	12.3	10.2	15.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.1	20.6	27.8
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.1	17.9	30.8
Base Number (BN)	mg KOH/g	ASTM D2896		6.6	7.4	7.1



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2

LLUID LHOLEK I IES		method			riistory i	Historyz	
Visc @ 100°C	cSt	ASTM D445	12.00	11.1	10.9	10.9	

Iron (ppm)		Le:	ad (ppm)	
Severe		80 - Sev	vere	
Alexand		E 60 Abo		
Abnormal		40 AD	normal	
m	3	0		
Apr29/23	Oct5/23	Feb 10/24	0ct5/23	
Aluminum (ppm)	Ch	romium (ppm)	
Severe		50 J Sev	vere	
Abnormal		30 Ab	normal	
Abroma		20	ionna	
m		ا ا	3	
Apr29/23	Oct5/23	Feb 10/24	0ct5/23	
Copper (ppm)			icon (ppm)	
Severe Abnormal		80 See	(ere	
		E.40		
		20 Abo	normal	
20	2	20 2	3	
Apr29/23	Oct5/23 ·	Feb 10/24	0ct5/23	
Viscosity @ 100	°C		se Number	
Abnormal		0.8 (b/H)0.3		
Base		Base Mumber (ng KOH/(g)		
Abnormal		N 2.0		
			3	
Apr29/23	Oct5/23 .	Feb10/24 Apr29/23	Oct5/23 ·	





Laboratory

Sample No.

: PCA0114576 Lab Number : 06095292 **Unique Number** : 10888145

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 21 Feb 2024

Tested : 23 Feb 2024

Diagnosed : 23 Feb 2024 - Wes Davis Test Package: MOB 1 (Additional Tests: TBN)

US 19116 Contact: ROSTY VITER rviter@millertransgroup.com T: (215)552-9832

Contact/Location: ROSTY VITER - MILPHINE

MILLER TRUCK LEASING #118

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (215)552-9892

2196 BENNETT ROAD

PHILADELPHIA, PA