

## **OIL ANALYSIS REPORT**

# (YA130651) 3675C

Component **Natural Gas Engine** 

PETRO CANADA DURON GEO LD 15W40 (35 GAL)

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0109505	GFL0058793	GFL0039491
Sample Date		Client Info		15 Feb 2024	02 Feb 2023	15 Aug 2022
Machine Age	hrs	Client Info		11872	11872	0
Oil Age	hrs	Client Info		1200	11872	0
Oil Changed		Client Info		Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	4	11	28
Chromium	ppm	ASTM D5185m	>4	<1	1	4
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	2	2	5
Lead	ppm	ASTM D5185m	>30	<1	0	<1
Copper	ppm	ASTM D5185m	>35	<1	2	4
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	42	38	49
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	50	49	55	51
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	560	566	691	504
Calcium	ppm	ASTM D5185m	1510	1493	1353	1393


Phosphorus	ppm	ASTM D5185m	780	765	846	771
Zinc	ppm	ASTM D5185m	870	949	1055	931
Sulfur	ppm	ASTM D5185m	2040	2488	3263	2565
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+100	4	3	13
Sodium		AOTH DELOF		•	4	C
ooulum	ppm	ASTM D5185m		2		6


INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.3	6.4	6.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.5	18.0	19.7
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.8	14.5	15.6
Base Number (BN)	ma KOH/a	ASTM D2896	10.2	8.5	8.9	10.4






## **OIL ANALYSIS REPORT**






VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.1	14.1	14.4	14.1
GRAPHS						

Ferrous Alloys



Non-ferrous Metals



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)