




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(LNY6655)
Machine Id
949007-205309

Component
Natural Gas Compression Engine
Fluid
PETRO CANADA DURON GEO LD 15W40 (28 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0092179	GFL0093228	GFL0083414
Sample Date	Client Info	19 Feb 2024	07 Sep 2023	16 Jun 2023
Machine Age	hrs	14255	13102	12435
Oil Age	hrs	14255	13102	12435
Oil Changed	Client Info	N/A	Changed	Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >4.0	<1.0	<1.0	<1.0
Water	WC Method >0.1	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >120	4	4	4
Chromium	ppm ASTM D5185m >10	<1	<1	<1
Nickel	ppm ASTM D5185m >5	<1	<1	<1
Titanium	ppm ASTM D5185m	0	0	<1
Silver	ppm ASTM D5185m >5	0	0	0
Aluminum	ppm ASTM D5185m >20	8	4	<1
Lead	ppm ASTM D5185m >40	0	<1	<1
Copper	ppm ASTM D5185m >300	<1	1	1
Tin	ppm ASTM D5185m >10	<1	<1	<1
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	<1

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 50	12	10	15
Barium	ppm ASTM D5185m 5	0	2	<1
Molybdenum	ppm ASTM D5185m 50	50	58	52
Manganese	ppm ASTM D5185m 0	<1	<1	<1
Magnesium	ppm ASTM D5185m 560	528	625	627
Calcium	ppm ASTM D5185m 1510	1444	1585	1570
Phosphorus	ppm ASTM D5185m 780	666	786	768
Zinc	ppm ASTM D5185m 870	922	1066	991
Sulfur	ppm ASTM D5185m 2040	2255	2970	2843

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	5	4	4
Sodium	ppm ASTM D5185m	10	19	7
Potassium	ppm ASTM D5185m >20	13	9	2

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844	0	0.1	0.1
Nitration	Abs/cm *ASTM D7624 >20	10.3	10.1	9.9
Sulfation	Abs/.1mm *ASTM D7415 >30	20.8	21.4	20.7

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	18.0	18.0	18.0
Base Number (BN)	mg KOH/g ASTM D2896 10.2	5.6	5.9	6.9







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.1	14.6	15.0	14.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0092179
Lab Number : 06096065
Unique Number : 10888918
Test Package : FLEET

Received : 21 Feb 2024
Tested : 22 Feb 2024
Diagnosed : 23 Feb 2024 - Sean Felton

GFL Environmental - 856 - Houston South
 8515 Highway 6 South
 Houston, TX
 US 77083
 Contact: Jose Gonzalez
 jgonzalez2@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: