




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
525012-7003

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- LTR)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0112768	GFL0101347	GFL0091768
Sample Date	Client Info	12 Feb 2024	22 Nov 2023	29 Sep 2023
Machine Age	hrs	17253	17080	16802
Oil Age	hrs	0	0	16802
Oil Changed	Client Info	Changed	Not Changd	Not Changd
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >90	19	17	8
Chromium	ppm ASTM D5185m >20	1	1	<1
Nickel	ppm ASTM D5185m >2	0	<1	0
Titanium	ppm ASTM D5185m >2	0	<1	0
Silver	ppm ASTM D5185m >2	0	0	0
Aluminum	ppm ASTM D5185m >20	3	2	6
Lead	ppm ASTM D5185m >40	1	2	<1
Copper	ppm ASTM D5185m >330	<1	1	4
Tin	ppm ASTM D5185m >15	<1	<1	<1
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	<1	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	4	3	2
Barium	ppm ASTM D5185m 0	0	<1	0
Molybdenum	ppm ASTM D5185m 60	56	61	62
Manganese	ppm ASTM D5185m 0	<1	<1	0
Magnesium	ppm ASTM D5185m 1010	877	953	926
Calcium	ppm ASTM D5185m 1070	947	1081	1033
Phosphorus	ppm ASTM D5185m 1150	969	980	1048
Zinc	ppm ASTM D5185m 1270	1174	1224	1266
Sulfur	ppm ASTM D5185m 2060	2716	3242	3522

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	6	7	4
Sodium	ppm ASTM D5185m	4	3	<1
Potassium	ppm ASTM D5185m >20	<1	2	5
Fuel	% ASTM D3524 >3.0	0.4	<1.0	<1.0

INFRA-RED




method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >6	0.4	0.3	0.2
Nitration	Abs/cm *ASTM D7624 >20	8.9	7.9	6.0
Sulfation	Abs/.1mm *ASTM D7415 >30	19.5	18.9	18.0

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	15.2	14.9	14.0
Base Number (BN)	mg KOH/g ASTM D2896 9.8	8.2	8.4	9.0







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.85	13.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0112768
 Lab Number : 06096144
 Unique Number : 10888997
 Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel)

Received : 21 Feb 2024
 Tested : 27 Feb 2024
 Diagnosed : 27 Feb 2024 - Wes Davis

GFL Environmental - 654 - Richmond Hauling
 11800 Lewis Road
 Chester, VA
 US 23831
 Contact: Jimmy Mayes
 jmayes@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: