


OIL ANALYSIS REPORT

Sample Rating Trend









729088
Component
Transmission (Auto)

PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

HD Synthetic 668	(GAL)	Jui	n2023	Jan2024 Feb20	24	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0103544	GFL0085344	GFL0085366
Sample Date		Client Info		15 Feb 2024	02 Jan 2024	28 Jun 2023
Machine Age	hrs	Client Info		26869	26380	25533
Oil Age	hrs	Client Info		26869	26380	0
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	ΓΙΟΝ	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METAI	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>220	44	32	32
Chromium	ppm	ASTM D5185m	>2	0	<1	0
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>75	11	5	10
Lead	ppm	ASTM D5185m	>95	12	1	2
Copper	ppm	ASTM D5185m		16	4	5
Tin	ppm	ASTM D5185m	>10	1	2	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		76	68	93
Barium	ppm	ASTM D5185m		0	0	2
Molybdenum	ppm	ASTM D5185m		0	1	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		0	2	2
Calcium	ppm	ASTM D5185m		46	124	138
Phosphorus	ppm	ASTM D5185m		191	224	244
Zinc	ppm	ASTM D5185m		0	0	16
Sulfur	ppm	ASTM D5185m		1291	1862	2111
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		5	6	5
Sodium	ppm	ASTM D5185m		4	<1	1
Potassium	ppm	ASTM D5185m	>20	1	1	<1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	LIGHT	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual	20.1	NEG	NEG	NEG
1100 Walei	Scalal	VISUAI		INLU	11LG	NLG





OIL ANALYSIS REPORT




FLUID PROPI	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	34	34.1	33.2	34.3
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

GRAPHS









Certificate L2367

Laboratory Sample No.

: GFL0103544 Lab Number : 06096554 Unique Number : 10889407 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 21 Feb 2024 Tested : 22 Feb 2024

Diagnosed

: 22 Feb 2024 - Wes Davis

GFL Environmental - 958A - Chillicothe Wigand

19908 N. State Rd 29 Chillicothe, IL US 61523

Contact: Stephanie Blount sblount@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: