


OIL ANALYSIS REPORT



NORMAL



PR7644

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- 0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

GAL)				Feb 2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0118832		
Sample Date		Client Info		15 Feb 2024		
Machine Age	mls	Client Info		8074		
Oil Age	mls	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATI	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	52		
Chromium	ppm	ASTM D5185m	>20	1		
Nickel	ppm	ASTM D5185m	>4	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	7		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m	>330	37		
Tin	ppm	ASTM D5185m	>15	3		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	53		
Barium	ppm	ASTM D5185m	0	<1		
Molybdenum	ppm	ASTM D5185m	50	38		
Manganese	ppm	ASTM D5185m	0	8		
Magnesium	ppm	ASTM D5185m	950	475		
Calcium	ppm	ASTM D5185m	1050	1523		
Phosphorus	ppm	ASTM D5185m	995	719		
Zinc	ppm	ASTM D5185m	1180	846		
Sulfur	ppm	ASTM D5185m	2600	2246		
CONTAMINAN		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	7		
Sodium	ppm	ASTM D5185m	. 00	6		
Potassium	ppm	ASTM D5185m	>20	13		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	% A la a /a ra	*ASTM D7844	>3	0.2		
Nitration	Abs/cm	*ASTM D7624	>20	6.5		
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.3		
FLUID DEGRAD			limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.0		
Base Number (BN)	mg KOH/g	ASTM D2896		9.8		



OIL ANALYSIS REPORT





Visc @ 100°C	cSt	ASTM D445	12.00	9.5		
GRAPHS						
Iron (ppm)				Lead (ppm	1)	
Severe				Severe		
O Abnormal				E 60 Abnormal		
1		***************************************		40 7 4		
0				20		
Feb15/24			Feb15/24	Feb15/24		
			虚		()	
Aluminum (ppm)				Chromium	(ppm)	
Severe			-	40 Severe		
Abnormal				Abnormal		
1				10+		
45				0 5		
Feb 15/24			Feb15/24	Feb15/24		
Copper (ppm)				Silicon (pp	m)	
Severe Abnormal		***************************************		80 - Severe		
)+				60		
)				Abnormal		
1				20		
Feb15/24 +			Feb15/24	Feb 15/24		
			型			
Viscosity @ 100°C	C			Base Num	ber 	
Abnormal			0000	KOH/g		
Base				6.0 per (m		
Abnormal				8.0 - 6.0 - 6.0 - 4.0 - 2.0 - 4.0 - 2.0 - 4.0 - 2.0 - 4.0 - 4.0 - 2.0 - 4.0 -		
3			-	0.0		
Feb15/24			Feb15/24	Feb15/24		





Certificate L2367

Laboratory Sample No.

Lab Number : 06096758 Unique Number: 10889611

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0118832

Test Package : MOB 1 (Additional Tests: TBN)

Received : 22 Feb 2024 **Tested** Diagnosed

: 23 Feb 2024 : 23 Feb 2024 - Sean Felton

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MILLER TRUCK LEASING #119

39 INDUSTRIAL AVE HASBROUCK HEIGHTS, NJ US 07604

Contact: MIKE LONGETTE

mlongette@millertransgroup.com T:

F: (201)528-7053