


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



5082 Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- 0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QTS)		Oct	2023	Dec2023 Feb202	14	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0118826	PCA0115243	PCA0106321
Sample Date		Client Info		13 Feb 2024	14 Dec 2023	18 Oct 2023
Machine Age	mls	Client Info		0	0	0
Oil Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	22	24	28
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	4	8
Lead	ppm	ASTM D5185m	>40	<1	<1	1
Copper	ppm	ASTM D5185m	>330	1	<1	2
Tin	ppm	ASTM D5185m	>15	1	<1	1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	2	6	13
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	63	67	68
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	956	1002	899
Calcium	ppm	ASTM D5185m	1050	1099	1186	1296
Phosphorus	ppm	ASTM D5185m	995	1043	1160	1138
Zinc	ppm	ASTM D5185m	1180	1207	1381	1306
Sulfur	ppm	ASTM D5185m	2600	2891	3133	2988
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	5	6
Sodium	ppm	ASTM D5185m		2	<1	1
Potassium	ppm	ASTM D5185m	>20	0	0	0
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1	1	1.2
Nitration	Abs/cm	*ASTM D7624	>20	10.4	11.0	11.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.3	22.0	22.2
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.2	19.2	19.7
Base Number (BN)	mg KOH/g	ASTM D2896		8.5	8.5	9.3



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.4	11.6	12.0

GRAPHS				
Iron (ppm)		Lead (ppm)	
200 Severe		Severe		
150 Abnormal	ļ	Abnormal		
1		107		
50		20		
	Dec14/23 -	Oct18/23	Dec14/23 -	Feb13/24 -
	Pec.			92
Aluminum (ppm)		Chromium	(ppm)	
40 Severe		40 Severe		
Abnormal		30 Abnormal		
10	1	20 Annormal		
0		0		
Oct18/23	Dec14/23	Oct18/23	Dec14/23	Feb13/24
Copper (ppm)		Silicon (ppr		Œ
400 Severe Publication		80 Severe	,	
300		60		
툂 200 -		Abnormal		
100		20		
23 0	23	23	23+	24
Oct18/23	Dec14/23	Oct18/23	Dec14/23	Feb13/24
Viscosity @ 100°C		Base Numb	per	
16 Abnormal		8.0		
14 Abnormal	Base Mumber from KOH/n)	6.0		
E12+	# DOCUMENT OF THE PROPERTY OF	4.0		
Abnormal Abnormal	200	2.0		
0ct18/23	Dec 14/23 +	0ct18/23	Dec14/23 -	Feb13/24
0001	Pecil Feb1	Oct1	Decl	Feb1

: 22 Feb 2024

: 23 Feb 2024

: 23 Feb 2024 - Wes Davis





Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Lab Number : 06096788 Unique Number : 10889641

: PCA0118826 Received

Tested Diagnosed

Test Package: MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MILLER TRUCK LEASING #119

39 INDUSTRIAL AVE HASBROUCK HEIGHTS, NJ US 07604

Contact: MIKE LONGETTE

mlongette@millertransgroup.com T:

F: (201)528-7053 Contact/Location: MIKE LONGETTE - MILRUT