


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **2227113**

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- Q

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QTS)			Dec2023	Feb2024		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0118403	PCA0106368	
Sample Date		Client Info		17 Feb 2024	17 Dec 2023	
Machine Age	mls	Client Info		0	40000	
Oil Age	mls	Client Info		20000	15000	
Oil Changed		Client Info		Not Changd	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	21	29	
Chromium	ppm	ASTM D5185m	>20	0	<1	
Nickel	ppm	ASTM D5185m	>4	<1	8	
Titanium	ppm	ASTM D5185m		1	<1	
Silver	ppm	ASTM D5185m	>3	0	6	
Aluminum	ppm	ASTM D5185m	>20	2	12	
Lead	ppm	ASTM D5185m	>40	<1	3	
Copper	ppm	ASTM D5185m	>330	5	420	
Tin	ppm	ASTM D5185m	>15	1	2	
Vanadium	ppm	ASTM D5185m		0	<1	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	2	12	
Barium	ppm	ASTM D5185m	0	0	<1	
Molybdenum	ppm	ASTM D5185m	50	54	67	
Manganese	ppm	ASTM D5185m	0	<1	1	
Magnesium	ppm	ASTM D5185m	950	827	893	
Calcium	ppm	ASTM D5185m	1050	1005	1155	
Phosphorus	ppm	ASTM D5185m	995	917	969	
Zinc	ppm	ASTM D5185m	1180	1113	1158	
Sulfur	ppm	ASTM D5185m	2600	2685	2624	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	17	
Sodium	ppm	ASTM D5185m		2	3	
Potassium	ppm	ASTM D5185m	>20	4	29	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.4	0.2	
Nitration	Abs/cm	*ASTM D7624	>20	9.7	8.8	
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.1	19.6	
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.0	16.4	
Base Number (BN)	mg KOH/g	ASTM D2896		6.6	7.2	




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROPE	ERITES	method			history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	10.3	

GRAPHS













Laboratory Sample No.

: PCA0118403 Lab Number : 06098159 Unique Number: 10896389 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

Diagnosed

: 23 Feb 2024 : 25 Feb 2024 : 25 Feb 2024 - Wes Davis

US 21802 Contact: RICHARD O'NEAL richard.oneal@perdue.com T: (410)543-3628

7036 ZION CHURCH ROAD

SALISBURY, MD

F: (410)341-2164

PERDUE FARMS - SALISBURY

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: RICHARD O'NEAL - PERSALMD