




OIL ANALYSIS REPORT

Sample Rating Trend



FUEL



Machine Id
427077-402331
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0107962	GFL0093574	GFL0093572
Sample Date	Client Info		21 Feb 2024	01 Feb 2024	29 Jan 2024
Machine Age	hrs	Client Info	18620	18538	18426
Oil Age	hrs	Client Info	0	328	216
Oil Changed	Client Info		Not Chngd	Not Chngd	Not Chngd
Sample Status			ABNORMAL	ABNORMAL	ABNORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	5	5	6
Chromium	ppm	ASTM D5185m >20	0	<1	<1
Nickel	ppm	ASTM D5185m >5	0	<1	<1
Titanium	ppm	ASTM D5185m >2	36	39	39
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >20	2	2	2
Lead	ppm	ASTM D5185m >40	0	0	<1
Copper	ppm	ASTM D5185m >330	<1	<1	<1
Tin	ppm	ASTM D5185m >15	<1	<1	<1
Vanadium	ppm	ASTM D5185m	0	<1	<1
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	26	41	48
Barium	ppm	ASTM D5185m 0	0	2	0
Molybdenum	ppm	ASTM D5185m 60	32	34	32
Manganese	ppm	ASTM D5185m 0	<1	0	0
Magnesium	ppm	ASTM D5185m 1010	611	687	647
Calcium	ppm	ASTM D5185m 1070	1217	1224	1267
Phosphorus	ppm	ASTM D5185m 1150	826	989	904
Zinc	ppm	ASTM D5185m 1270	916	1156	1112
Sulfur	ppm	ASTM D5185m 2060	2806	3311	3440

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	3	5	5
Sodium	ppm	ASTM D5185m	5	0	0
Potassium	ppm	ASTM D5185m >20	0	2	3
Fuel	%	ASTM D3524 >3.0	▲ 4.9	▲ 3.7	▲ 4.0

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	0.2	0.2	0.1
Nitration	Abs/cm	*ASTM D7624 >20	9.4	8.6	8.3
Sulfation	Abs/.1mm	*ASTM D7415 >30	20.4	18.9	18.3


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	16.5	14.9	14.6
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	5.6	6.3	7.4




OIL ANALYSIS REPORT


▲ Fuel Dilution



▲ Viscosity @ 100°C



Base Number




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4 ▲ 12.4	12.8	12.9

GRAPHS


Ferrous Alloys




Non-ferrous Metals



▲ Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : GFL0107962

Lab Number : 06098269

Unique Number : 10896499

Test Package : FLEET (Additional Tests: PercentFuel)

Received : 23 Feb 2024

Tested : 27 Feb 2024

Diagnosed : 27 Feb 2024 - Wes Davis

GFL Environmental - 891 - Oklahoma City Hauling

1001 South Rockwell

Oklahoma City, OK

US 73128

Contact: Andy Smith

andrew.smith@gflenv.com

T: (405)306-1651

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)