




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
834045
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (--- GAL)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0108065	GFL0108130	GFL0102468
Sample Date	Client Info		17 Feb 2024	23 Jan 2024	30 Dec 2023
Machine Age	hrs	Client Info	988	857	771
Oil Age	hrs	Client Info	857	0	0
Oil Changed	Client Info		N/A	Not Changd	Not Changd
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	84	71	62
Chromium	ppm	ASTM D5185m >20	2	<1	<1
Nickel	ppm	ASTM D5185m >5	2	2	2
Titanium	ppm	ASTM D5185m >2	0	0	0
Silver	ppm	ASTM D5185m >2	0	0	<1
Aluminum	ppm	ASTM D5185m >20	8	6	6
Lead	ppm	ASTM D5185m >40	4	2	2
Copper	ppm	ASTM D5185m >330	19	17	16
Tin	ppm	ASTM D5185m >15	2	2	2
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 50	3	4	7
Barium	ppm	ASTM D5185m 5	4	2	2
Molybdenum	ppm	ASTM D5185m 50	67	60	62
Manganese	ppm	ASTM D5185m 0	16	14	14
Magnesium	ppm	ASTM D5185m 560	940	815	872
Calcium	ppm	ASTM D5185m 1510	1447	1247	1291
Phosphorus	ppm	ASTM D5185m 780	843	765	811
Zinc	ppm	ASTM D5185m 870	1052	907	1000
Sulfur	ppm	ASTM D5185m 2040	2315	2233	2475

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	33	32	33
Sodium	ppm	ASTM D5185m	9	6	6
Potassium	ppm	ASTM D5185m >20	8	6	6

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	0	0	0.2
Nitration	Abs/cm	*ASTM D7624 >20	14.3	13.7	11.8
Sulfation	Abs/.1mm	*ASTM D7415 >30	26.1	25.3	23.7

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	24.9	23.5	21.2
Base Number (BN)	mg KOH/g	ASTM D2896 10.2	4.4	4.2	4.0







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.1	14.1	14.2	14.3

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0108065 **Received** : 26 Feb 2024
Lab Number : **06100781** **Tested** : 27 Feb 2024
Unique Number : 10899011 **Diagnosed** : 27 Feb 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 837 - Harrison TS
 22820 S State Route 291
 Harrisonville, MO
 US 64701
 Contact: JOHNNY PEREZ
 johnny.perez@gflenv.com
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)