


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



946027-260305

Component

Natural Gas Engine

PETRO CANADA DURON GEO LD 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


GAL)		Feb 2022 M	ar2022 Nov2022 Feb	2023 Apr2023 May2023	Dec2023	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0106818	GFL0091999	GFL0084747
Sample Date		Client Info		22 Feb 2024	15 Dec 2023	21 Jun 2023
Machine Age	hrs	Client Info		2736	2161	0
Oil Age	hrs	Client Info		600	600	0
Oil Changed		Client Info		Changed	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METAI	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	9	24	3
Chromium	ppm	ASTM D5185m	>4	<1	2	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	4	6	1
Lead	ppm	ASTM D5185m	>30	0	2	0
Copper	ppm	ASTM D5185m	>35	<1	4	0
Tin	ppm	ASTM D5185m	>4	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	3	2	41
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	50	48	60	48
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	560	524	713	623
Calcium	ppm	ASTM D5185m	1510	1399	1414	1444
Phosphorus	ppm	ASTM D5185m	780	655	759	781
Zinc	ppm	ASTM D5185m	870	885	1087	960
Sulfur	ppm	ASTM D5185m	2040	2210	2585	3013
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+100	3	10	8
Sodium	ppm	ASTM D5185m		4	17	2
Potassium	ppm	ASTM D5185m	>20	0	16	<1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	10.2	11.6	5.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	24.5	19.0
FLUID DEGRA	ADATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.6	18.9	15.5
D 11 (510)	1/011/	AOTH DOCCO	100		0.0	0.0

Base Number (BN) mg KOH/g ASTM D2896 10.2 5.0



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPI	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.1	14.6	14.6	14.9

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number : 06100851

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Test Package : FLEET

: GFL0106818

Unique Number : 10899081

Received **Tested** Diagnosed

: 26 Feb 2024 : 27 Feb 2024 : 27 Feb 2024 - Wes Davis

GFL Environmental - 856 - Houston South

8515 Highway 6 South Houston, TX US 77083

Contact: Apolinar Zacarias pzacariascano@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: