

OIL ANALYSIS REPORT


NORMAL



MACK 129060-SW8905

Component **Diesel Engine**

MOBIL DELVAC ELITE 15W40 (--- GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

15W40 (GA	L)			Feb 2024		
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0111343		
Sample Date		Client Info		12 Feb 2024		
Machine Age	hrs	Client Info		10231		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINA	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAI	LS	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>120	4		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>5	0		
Titanium	ppm	ASTM D5185m	>2	0		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>20	3		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m	>330	8		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		94		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		117		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		653		
Calcium	ppm	ASTM D5185m		1237		
Phosphorus	ppm	ASTM D5185m		705		
Zinc	ppm	ASTM D5185m		798		
Sulfur	ppm	ASTM D5185m		3119		
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	4		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.2		
Nitration	Abs/cm	*ASTM D7624	>20	9.6		
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.5		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.8		



Feb12/24


OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		


FLUID PROPE	ERITES	method	limit/base		history1	history2
Visc @ 100°C	cSt	ASTM D445	15.2	12.9		

GRAPHS



10-	Non-ferrous	Metals					
8-	copper lead						
mdd							
4							
2 -							
0 -	Feb12/24	***************************************	***************************************	***************************************	************************	ξ 	
	\ //	0000					







Laboratory Sample No. Lab Number : 06101343

: GFL0111343 Unique Number : 10899573 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 27 Feb 2024 **Tested**

: 28 Feb 2024 Diagnosed : 28 Feb 2024 - Don Baldridge

GFL Environmental - 981 - Port Arthur Hauling

1000 S Business Park Dr Port Arthur, TX US 77640

Contact: MICHAEL KAY mkay@gflenv.com

T: (336)660-9331

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)