

## **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

# Machine Id 920085-205325

#### Component Diesel Engine

Fluid

PETRO CANADA DURON SHP 15W40 (--- GAL)

## DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


### Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| SAMPLE INFOR  | MATION  | method   | limit/base  | current   | history1   | history2  |
|---|---|--|---|---|--|---|
| Sample Number   |   | Client Info  |   | GFL0087914  | GFL0060283   | GFL0060285  |
| Sample Date   |   | Client Info  |   | 27 Feb 2024   | 12 Dec 2022  | 22 Sep 2022   |
| Machine Age   | hrs   | Client Info  |   | 0   | 7942   | 7800  |
| Oil Age   | hrs   | Client Info  |   | 600   | 580  | 590   |
| Oil Changed   |   | Client Info  |   | Changed   | Changed  | Changed   |
| Sample Status   |   |  |   | NORMAL  | NORMAL   | NORMAL  |
| CONTAMINAT  | ION   | method   | limit/base  | current   | history1   | history2  |
| Fuel  |   | WC Method  | >5  | <1.0  | <1.0   | <1.0  |
| Water   |   | WC Method  | >0.2  | NEG   | NEG  | NEG   |
| Glycol  |   | WC Method  |   | NEG   | NEG  | NEG   |
| WEAR METAL  | S   | method   | limit/base  | current   | history1   | history2  |
| Iron  | ppm   | ASTM D5185m  | >100  | 63  | 17   | 13  |
| Chromium  | ppm   | ASTM D5185m  | >20   | 5   | 1  | <1  |
| Nickel  | ppm   | ASTM D5185m  | >4  | ۲<br>۲  | <1   | 0   |
| Titanium  | ppm   | ASTM D5185m  | - T   | <1  | 0  | 0   |
| Silver  | ppm   | ASTM D5185m  | >3  | 0   | 0  | 0   |
| Aluminum  | ppm   | ASTM D5185m  | >20   | 10  | 2  | 2   |
| Lead  | ppm   | ASTM D5185m  | >40   | 0   | <1   | 2   |
| Copper  | ppm   |  | >330  | <1  | <1   | <1  |
| Tin   | ppm   | ASTM D5185m  | >15   | <1  | <1   | <1  |
| Vanadium  | ppm   | ASTM D5185m  | 10  | 0   | 0  | 0   |
| Cadmium   | ppm   | ASTM D5185m  |   | 0   | 0  | 0   |
|   | 1-1-  |  |   |   |  |   |
| ADDITIVES   |   | method   | limit/base  | current   | history1   | history2  |
| ADDITIVES   | ppm   |  |   |   | history1   | history2  |
| Boron   | ppm   | ASTM D5185m  | 0   | 2   | 1  | 2   |
| Boron<br>Barium   | ppm   | ASTM D5185m<br>ASTM D5185m   | 0   | 2<br>0  | 1<br>0   | 2<br>0  |
| Boron<br>Barium<br>Molybdenum   | ppm<br>ppm  | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60  | 2<br>0<br>62  | 1<br>0<br>58   | 2<br>0<br>60  |
| Boron<br>Barium<br>Molybdenum<br>Manganese  | ppm<br>ppm<br>ppm   | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m   | 0<br>0<br>60<br>0   | 2<br>0<br>62<br><1  | 1<br>0<br>58<br><1   | 2<br>0<br>60<br><1  |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium   | ppm<br>ppm<br>ppm<br>ppm  | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60<br>0<br>1010   | 2<br>0<br>62<br><1<br>970   | 1<br>0<br>58<br><1<br>1006   | 2<br>0<br>60<br><1<br>957   |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium  | ppm<br>ppm<br>ppm<br>ppm<br>ppm   | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m   | 0<br>0<br>60<br>0<br>1010<br>1070   | 2<br>0<br>62<br><1<br>970<br>1069   | 1<br>0<br>58<br><1<br>1006<br>1111   | 2<br>0<br>60<br><1<br>957<br>1102   |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus  | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm  | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60<br>0<br>1010<br>1070<br>1150   | 2<br>0<br>62<br><1<br>970<br>1069<br>986  | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010   | 2<br>0<br>60<br><1<br>957<br>1102<br>983  |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium  | ppm<br>ppm<br>ppm<br>ppm<br>ppm   | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60<br>0<br>1010<br>1070   | 2<br>0<br>62<br><1<br>970<br>1069   | 1<br>0<br>58<br><1<br>1006<br>1111   | 2<br>0<br>60<br><1<br>957<br>1102   |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc  | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm   | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60<br>0<br>1010<br>1070<br>1150<br>1270   | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253  | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320   | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354  |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur  | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm  | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60<br>0<br>1010<br>1070<br>1150<br>1270<br>2060   | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br>current   | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482   | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314  |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN  | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>TS                                    | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60<br>1010<br>1070<br>1150<br>1270<br>2060  | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958  | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1   | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br>history2  |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon   | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm  | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br><b>method</b><br>ASTM D5185m   | 0<br>0<br>60<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br><b>limit/base</b>  | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br>current<br>6  | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3  | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br>history2<br>4   |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon<br>Sodium   | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>TS                                    | ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br>ASTM D5185m<br><b>method</b><br>ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>60<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br><b>limit/base</b>  | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br>current<br>6<br>2   | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3<br>2   | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br>history2<br>4<br>2  |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon<br>Sodium<br>Potassium  | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>TS<br>ppm<br>ppm<br>ppm               | ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br>2060<br>225<br>>25   | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br><u>current</u><br>6<br>2<br>13<br><u>current</u>                  | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3<br>2<br>5<br>5<br>history1                                     | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br><b>history2</b><br>4<br>2<br>6<br><b>history2</b>                       |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon<br>Sodium<br>Potassium<br>INFRA-RED<br>Soot %                           | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm                            | ASTM D5185m<br>ASTM D5185m  | 0<br>0<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br>2060<br>225<br>>25<br>>20<br>Limit/base<br>>20   | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br><u>current</u><br>6<br>2<br>13<br><u>current</u><br>2             | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3<br>2<br>5<br>5<br>history1<br>1.3                              | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br>history2<br>4<br>2<br>6<br>6<br>history2<br>1.1                         |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon<br>Sodium<br>Potassium<br>INFRA-RED<br>Soot %<br>Nitration              | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>TS<br>ppm<br>ppm<br>ppm               | ASTM D5185m<br>ASTM D5185m   | 0<br>0<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br>2060<br>225<br>220<br>220<br>220<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20                                   | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br><i>current</i><br>6<br>2<br>13<br><i>current</i><br>2<br>13.      | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3<br>2<br>5<br>history1<br>1.3<br>9.7                            | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br>history2<br>4<br>2<br>6<br>history2                                     |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon<br>Sodium<br>Potassium<br>INFRA-RED<br>Soot %                           | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm                            | ASTM D5185m<br>ASTM D5185m                              | 0<br>0<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br>2060<br>225<br>>25<br>>20<br>Limit/base<br>>20   | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br><u>current</u><br>6<br>2<br>13<br><u>current</u><br>2             | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3<br>2<br>5<br>5<br>history1<br>1.3                              | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br><b>history2</b><br>4<br>2<br>6<br><b>history2</b><br>1.1<br>9.8<br>22.0 |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon<br>Sodium<br>Potassium<br>INFRA-RED<br>Soot %<br>Nitration<br>Sulfation | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>TS<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm | ASTM D5185m<br>ASTM D7844<br>*ASTM D7624<br>*ASTM D7415 | 0<br>0<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br>2060<br>225<br>20<br>220<br>220<br>20<br>3<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20<br>20 | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br>current<br>6<br>2<br>13<br>current<br>2<br>13<br>current          | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3<br>2<br>5<br><u>history1</u><br>1.3<br>9.7<br>22.3<br>history1 | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br>history2<br>4<br>2<br>6<br>history2<br>1.1<br>9.8<br>22.0<br>history2   |
| Boron<br>Barium<br>Molybdenum<br>Manganese<br>Magnesium<br>Calcium<br>Phosphorus<br>Zinc<br>Sulfur<br>CONTAMINAN<br>Silicon<br>Sodium<br>Potassium<br>INFRA-RED<br>Soot %<br>Nitration<br>Sulfation | ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm<br>ppm                            | ASTM D5185m<br>ASTM D5185m                              | 0<br>0<br>0<br>1010<br>1070<br>1150<br>1270<br>2060<br>2060<br>225<br>20<br>225<br>20<br>20<br>320<br>33<br>20<br>20<br>20  | 2<br>0<br>62<br><1<br>970<br>1069<br>986<br>1253<br>2958<br><u>current</u><br>6<br>2<br>13<br><u>current</u><br>2<br>13<br>22 | 1<br>0<br>58<br><1<br>1006<br>1111<br>1010<br>1320<br>3482<br>history1<br>3<br>2<br>5<br><u>history1</u><br>1.3<br>9.7<br>22.3             | 2<br>0<br>60<br><1<br>957<br>1102<br>983<br>1354<br>3314<br><b>history2</b><br>4<br>2<br>6<br><b>history2</b><br>1.1<br>9.8<br>22.0 |




# **OIL ANALYSIS REPORT**





| VISUAL           |        | method    | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Yellow Metal     | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Precipitate      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Silt             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Debris           | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Sand/Dirt        | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Appearance       | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Odor             | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Emulsified Water | scalar | *Visual   | >0.2       | NEG     | NEG      | NEG      |
| Free Water       | scalar | *Visual   |            | NEG     | NEG      | NEG      |
| FLUID PROPE      | RTIES  | method    | limit/base | current | history1 | history2 |
| Visc @ 100°C     | cSt    | ASTM D445 | 15.4       | 13.7    | 14.4     | 14.4     |
| GRAPHS           |        |           |            |         |          |          |





Certificate L2367

F: