


OIL ANALYSIS REPORT

(89819X) Walgreens - Tractor [Walgreens - Tractor] 136A68031

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0110564	PCA0093475	PCA0093510
Sample Date		Client Info		23 Feb 2024	15 Sep 2023	23 May 2023
Machine Age	mls	Client Info		214600	203228	192675
Oil Age	mls	Client Info		214600	10553	192631
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATI	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method		NEG	NEG	NEG
Glycol		WC Method	7 U.L	NEG	NEG	NEG
	0		limit/booo			
WEAR METALS	>	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	24	22	24
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m		4	14	3
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>30	4	1	2
Lead	ppm	ASTM D5185m	>30	0	0	0
Copper	ppm	ASTM D5185m	>150	2	1	2
Tin	ppm	ASTM D5185m	>5	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	16	17	8
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	54	45	55
Manganese	ppm		0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	746	821	894
Calcium	ppm		1050	1180	1246	1217
Phosphorus	ppm	ASTM D5185m	995	935	925	988
Zinc	ppm	ASTM D5185m	1180	1198	1187	1269
Sulfur	ppm	ASTM D5185m	2600	3241	3342	3654
CONTAMINAN'		method	limit/base	current	history1	history2
		ASTM D5185m				7
Silicon	ppm		>20	5	6	
Sodium	ppm	ASTM D5185m	00	3	2	2
Potassium	ppm	ASTM D5185m	>20	2	1	1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6	0.6	0.6
Nitration	Abs/cm	*ASTM D7624	>20	10.7	10.4	10.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.9	21.6	22.9
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.2	17.0	20.2
Base Number (BN)	mg KOH/g	ASTM D2896		5.7	5.6	5.5
	3 3					



OIL ANALYSIS REPORT





Sep15/23


VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method			history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.5	11.0	11.3

GRAPHS













Certificate L2367

Laboratory Sample No.

: PCA0110564 Lab Number : 06104782 Unique Number : 10903012 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 29 Feb 2024

Tested : 01 Mar 2024 Diagnosed : 01 Mar 2024 - Wes Davis

Transervice - Shop 1376 - Berkeley-Linden

3425 Tremley Point Road Linden, NJ US 07036

Contact: Shop 1376 Oil Analysis shop1376@transervice.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: